

DISPERBYK-2117

Solvent-free wetting and dispersing additive for solvent-borne and solvent-free pigment concentrates and printing inks (medium-polarity to polar). Main use is to disperse carbon blacks and phthalocyanine pigments.

Product Data

Composition

Block copolymer with pigment affinic groups

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Amine value: 24 mg KOH/g
Density (68 °F): 8.62 lbs/US gal
Non-volatile matter (10 min., 302 °F): 100 %

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Applications

Coatings and Printing Inks

Special Features and Benefits

DISPERBYK-2117 defloculates pigments and stabilizes them by means of steric hindrance. The defloculating property of the additive results in increased gloss, color intensity, transparency or hiding power and a reduced mill base viscosity. DISPERBYK-2117 is recommended for use in pigment concentrates and solvent-borne printing inks, particularly for medium-polarity to polar flexographic and gravure printing inks based on alcohol-soluble cellulose nitrates. Main use is to disperse carbon blacks and phthalocyanine pigments (blue and green). BYK-SYNERGIST 2102 supports the effect of DISPERBYK-2117 with regard to the color strength development and the flow behavior.

Recommended Use

Pigment concentrates	<input checked="" type="checkbox"/>
Printing inks	<input checked="" type="checkbox"/>
Industrial coatings	<input type="checkbox"/>
Automotive coatings	<input type="checkbox"/>

especially recommended recommended

DISPERBYK-2117

Data Sheet
Issue 01/2014

Recommended Levels

Amount of additive (as supplied) based upon pigment:

Inorganic pigments:	5-10 %
Titanium dioxides:	1-5 %
Organic pigments:	20-40 %
Carbon blacks:	10-75 %

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

Wetting and dispersion additives should generally be added to the millbase. Only in this way can they be fully effective. In the case of binder-free grinds, the solvent components of the millbase are pre-mixed with the additive whilst stirring and before the pigment is added. If the grinds contain binder, the binder, solvent, and additive should be homogenized prior to adding the pigment.



Additive Guide



BYK USA Inc.
524 South Cherry Street
P.O. Box 5670
Wallingford, CT 06492
USA
Tel 203 265-2086
Fax 203 284-9158

cs.usa@byk.com
www.byk.com/additives

ACTAL®, ADJUST®, ADVITROL®, ALUFERSOL®, ANTI-TERRA®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CLAYTONE®, CLOISITE®, COPISIL®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, FULGEL®, FULMONT®, GARAMITE®, GELWHITE®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, NANOBYPK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, SILBYK®, TIXOGEL®, VISCOBYK®, Y-25®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAX®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.

This issue replaces all previous versions – Printed in the USA