

BYKJET-9150

High molecular weight wetting and dispersing additive for solvent-free UV-curable inkjet inks. Suitable for all pigment types.

Product Data

Composition

Solution of a structured copolymer with pigment-affinic groups


Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Amine value: 12 mg KOH/g
Acid value: 5 mg KOH/g
Active substance: 70 %
Density (20 °C): 1.07 g/ml
Solvents: Propoxylated neopentyl glycol diacrylate (PONPGDA)

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.



Applications

Inkjet Inks

Special Features and Benefits

High molecular weight wetting and dispersing additive for solvent-free, UV-curable inkjet inks. The additive improves pigment wetting and, thanks to its outstanding steric stabilization of the pigments, it also improves the optical properties of the systems (color strength, gloss, haze, transparency). The viscosity of the pigment concentrates and the finished inkjet inks is reduced and thixotropy prevented. Long-term stability without viscosity change is achieved. BYKJET-9150 also generates a uniform electrical charge across the pigment particles, thereby preventing possible co-flocculation of particles that are not equally charged. The excellent deflocculation causes a very small particle size and a narrow particle size distribution, which achieves short filtration times.

Recommended Use

BYKJET-9150 is suitable for all solvent-free, UV-curable inkjet inks. It stabilizes the majority of the pigments that are usually used in inkjet inks.

Recommended Levels

40-100 % additive (as supplied) based on organic pigments.

45-120 % additive (as supplied) based on carbon black pigments.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

Wetting and dispersing additives should generally be added to the millbase. Only in this way can they be fully effective. Pre-mix the resin and reactive thinner of the millbase and then gradually let the additive flow in whilst stirring. Only add the pigments when the additive has been thoroughly distributed.



Additive Guide



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABEN®, BENTOLITE®, CLAYTONE®, CLOISITE®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, TIXOGEL®, and VISCOSEAL® are registered trademarks of BYK Additives. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions – Printed in Germany