

# BYKJET-9170

High molecular weight wetting and dispersing additive for aqueous inkjet inks.  
Suitable for all pigment types.

## Product Data

### Composition

Solution of a structured copolymer with pigment-affinic groups


### Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Amine value:	7 mg KOH/g
Acid value:	7 mg KOH/g
Density (20 °C):	1.06 g/ml
Non-volatile matter (20 min., 150 °C):	40 %
Solvents:	Water
pH value:	7.4

### Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit [www.byk.com](http://www.byk.com) for further information.



## Applications

### Injek Inks

#### Special Features and Benefits

High molecular weight wetting and dispersing additive for solvent-borne inkjet inks. The additive improves pigment wetting and, thanks to its outstanding steric stabilization of the pigments, it also improves the optical properties of the systems (color strength, gloss, haze, transparency). The viscosity of the pigment concentrates and the finished inkjet inks is reduced and thixotropy prevented. Long-term stability without viscosity change is achieved. The excellent deflocculation causes a very small particle size and a narrow particle size distribution, which achieves short filtration times.

#### Recommended Use

BYKJET-9170 is suitable for all aqueous inkjet inks. It stabilizes the majority of the pigments that are usually used in inkjet inks.

## Recommended Levels

60-125 % additive (as supplied) based on organic pigments.

90-160 % additive (as supplied) based on carbon black pigments.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

## Incorporation and Processing Instructions

Wetting and dispersing additives should generally be added to the millbase. Only in this way can they be fully effective. If the grinds contain binder, gradually let the additive flow into the grinding resin co-solvent blend or the shear-stable emulsion. In the case of binder-free grinds, simply mix the additive with the water. Only add the pigments when the additive has been thoroughly distributed.



Additive Guide



**BYK-Chemie GmbH**  
P.O. Box 10 02 45  
46462 Wesel  
Germany  
Tel +49 281 670-0  
Fax +49 281 65735

[info@byk.com](mailto:info@byk.com)  
[www.byk.com/additives](http://www.byk.com/additives)

ACTAL®, ADJUST®, ADVITROL®, ALUFERSOL®, ANTI-TERRA®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CLAYTONE®, CLOISITE®, COPISIL®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, FULGEL®, FULMONT®, GARAMITE®, GELWHITE®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, SILBYK®, TIXOGEL®, VISCOBYK®, Y-25®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

This information is given to the best of our knowledge. Because of the multitude of formulations, production, and application conditions, all the above-mentioned statements have to be adjusted to the circumstances of the processor. No liabilities, including those for patent rights, can be derived from this fact for individual cases.

This issue replaces all previous versions – Printed in Germany