

BYK-310

Silicone-containing surface additive for solvent-free and solvent-borne coating systems, printing inks, adhesive systems and ambient-curing plastic systems with a strong reduction in the surface tension. Thermostable up to 210 °C.

Product Data

Composition

Solution of a polyester-modified polydimethylsiloxane.

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (20 °C):	0.91 g/ml
Non-volatile matter (10 min., 150 °C):	25 %
Solvents:	Xylene
Flash point:	25 °C

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Separation or turbidity may occur at temperatures below 5 °C. Warm to 20 °C and mix well.

Applications

Coatings Industry

Special Features and Benefits

The additive provides a strong reduction of the surface tension of coating systems. It therefore particularly improves substrate wetting and avoids cratering. Surface slip and gloss are also increased. BYK-310 is a thermostable silicone additive which, in contrast to conventional silicones, shows no thermal decomposition at temperatures between 150 °C and 230 °C. Consequently, when re-coating, no loss in adhesion and no surface defects occur, which can be caused by the decomposition products of conventional silicones above 150 °C.

Recommended Use

The additive is particularly recommended for all solvent-borne coatings and can also be used in solvent-free systems.

Recommended Levels

0.05-0.3 % additive (as supplied) based upon total formulation. In solvent-free systems up to 0.5 %.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive can be incorporated during any stage of the production process, including post-addition.

Special Note

Unlike so-called silicone oils, this additive is very user-friendly. Nevertheless, it should be determined in series testing, whether foam is stabilized in certain systems. Similarly, the recoatability, the migration of silicone in stacked sheets as well as cratering should be checked.

Printing Inks**Special Features and Benefits**

The additive provides a strong reduction of the surface tension of the systems. It therefore particularly improves substrate wetting and avoids cratering. Surface slip and gloss are also increased.

Recommended Use

Recommended for all solvent-borne printing inks.

Recommended Levels

0.05-0.3 % additive (as supplied) based upon total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive can be incorporated during any stage of the production process, including post-addition.

Special Note

Unlike so-called silicone oils, this additive is very user-friendly. Nevertheless, it should be determined in series testing, whether foam is stabilized in certain systems. Similarly, the recoatability and cratering should be checked.

Adhesives & Sealants

Special Features and Benefits

BYK-310 is a highly effective silicone additive. It provides a strong reduction of the surface tension, thereby improving the wetting of critical substrates.

Recommended Use

Recommended for improving the substrate wetting of epoxy-based adhesive systems.

Recommended Levels

0.05-0.3 % additive (as supplied) based upon total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive can be incorporated during any stage of the production process, including post-addition.

Special Note

Unlike so-called silicone oils, this additive is very user friendly. Nevertheless, its influence on the adhesive properties should be checked.

Ambient-curing Plastic Systems

Special Features and Benefits

BYK-310 is a highly effective silicone additive. It provides a strong reduction of the surface tension, thereby improving the wetting of critical substrates. It also exhibits high temperature stability.

Recommended Use

Recommended for improving the substrate wetting of ambient-curing epoxy-based resin systems.

Recommended Levels

0.05-0.3 % additive (as supplied) based upon total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive can be incorporated during any stage of the production process, including post-addition.

Special Note

Unlike so-called silicone oils, this additive is very user friendly. Nevertheless, it should be determined in series testing, whether surface defects occur in certain systems.

BYK-310

Data Sheet
Issue 11/2012

BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735
info@byk.com
www.byk.com/additives

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

This information is given to the best of our knowledge. Because of the multitude of formulations, production, and application conditions, all the above-mentioned statements have to be adjusted to the circumstances of the processor. No liabilities, including those for patent rights, can be derived from this fact for individual cases.

This issue replaces all previous versions – Printed in Germany