

DISPERBYK-109

Solvent-free wetting and dispersing additive for solvent-borne, medium-polar to non-polar coating systems to improve color acceptance of universal pastes in TPA or alkyd resin coatings.

Product Data

Composition

High molecular weight alkylolamino amide

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Amine value: 140 mg KOH/g
Density (68 °F): 7.93 lbs/US gal

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Separation or turbidity possible during storage or transport under 50 °F. Warm to 30-60 °C (86-140 °F) and mix well.

Special Note

Due to the high amine value, drying of alkyd resins can be impacted by overdosing.

Applications

Coatings Industry

Special Features and Benefits

By using DISPERBYK-109, the color acceptance of medium- to non-polar coating systems is greatly improved. DISPERBYK-109 can also be post-added to the coating system. However, this should be done before the addition of the color paste. DISPERBYK-109 is primarily used in coatings on alkyd resin basis and thermoplastic acrylics to disperse inorganic pigments (titanium dioxide and fillers).

Recommended Levels

1-2 % additive (as supplied) based upon titanium dioxide. As post-additive to improve color acceptance:
0.3-1 % additive (as supplied) based upon total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

DISPERBYK-109

Data Sheet
Issue 09/2012

Incorporation and Processing Instructions

For optimum performance, the additive must be incorporated into the millbase before addition of pigments. The resin and solvent components of the millbase are pre-mixed and then the additive is slowly incorporated while stirring continuously. Do not add the pigments until the additive has been fully distributed. To improve color acceptance, the additive can also be post-added into the coating.

Special Note

When added at concentrations of 1 % or higher (based upon total formulation), the effects on drying and yellowing should be tested.