

MINERPOL 220

Wax paste based on polyethylene wax for solvent-borne offset printing inks to improve surface slip, antiblocking and scratch resistance as well as abrasion resistance.

Product Data

Composition

Polyethylene wax dispersion

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Non-volatile matter (1h, 125 °C): 90 %
Carrier: Linseed oil/mineral oil 6/1
Melting point (wax content): 120 °C
Particle size (Hegman): < 25 µm
Viscosity (23 °C, D=50/s): 10000 mPa·s

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Temperature sensitive. To be stored and transported at a temperature below 35 °C. Mix well before use.

Applications

Printing Inks

Special Features and Benefits

The additive is recommended for offset printing inks to increase surface slip and gloss. It improves scratch resistance, abrasion resistance and antiblocking.

Recommended Levels

2-6 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive should be added early in the production process to ensure thorough distribution. If added later, ensure the mix is sufficiently dispersed. Mix well before use.

MINERPOL 220

Data Sheet
Issue 08/2013



Additive Guide



Google play

BYK-Chemie GmbH

P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com/additives

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

This information is given to the best of our knowledge. Because of the multitude of formulations, production, and application conditions, all the above-mentioned statements have to be adjusted to the circumstances of the processor. No liabilities, including those for patent rights, can be derived from this fact for individual cases.

This issue replaces all previous versions – Printed in Germany