

DISPERBYK-185

Solvent-free wetting and dispersing additive for solvent-borne and aqueous industrial coatings as well as architectural coatings. Particularly suitable for glycol-free universal pastes.

Product Data

Composition

Solution of a high molecular weight block copolymer with pigment affinic groups

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Amine value:	17 mg KOH/g
Density (68 °F):	9.39 lbs/US gal
Non-volatile matter (60 min., 221 °F):	> 90 %
Solvents:	Polyethylene glycol
Flash point:	244 °F

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Separation or turbidity may occur at temperatures below 5 °C (41 °F). Warm to 20 °C (68 °F) and mix well.

Special Note

The additive contains 52 % active substance and 48 % polyethylene glycol.

Applications

Coatings Industry and Leather Finishes

Special Features and Benefits

The additive deflocculates pigments by steric stabilization. The small particle size of the deflocculated pigments can achieve high levels of gloss and improved color strength. Transparency and hiding power also increase and viscosity is reduced. This also improves leveling and enables higher pigmentation levels.

Recommended Use

DISPERBYK-185 is solvent-free and is particularly suitable for the manufacture of alkylphenol-ethoxylate-free and solvent-free universal colorants used in aqueous, solvent-borne and solvent-free coatings.

DISPERBYK-185

Data Sheet
Issue 04/2016

Recommended Levels

Amount of additive (as supplied) based upon pigment:

Inorganic pigments: 10-15 %
Titanium dioxides: 3-6 %
Organic pigments: 20-45 %
Carbon blacks: 60-80 %

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

For optimum performance, the additive must be added slowly to the grinding resin/co-solvent mixture or to the shear-stable emulsion while stirring. Add the pigments only once the additive has been properly dispersed.

Special Note

If used in aqueous systems, a portion of the amine for pH control may be omitted due to the alkaline nature of the additive. Aqueous coatings may be critical with respect to their storage stability. It is generally recommended to test the long-term stability of the entire system.



BYK USA Inc.
524 South Cherry Street
P.O. Box 5670
Wallingford, CT 06492
USA
Tel 203 265-2086
Fax 203 284-9158

cs.usa@byk.com
www.byk.com

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYPK®, PAPERBYK®, SCONA®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABEN®, BENTOLITE®, CLAYTONE®, CLOISITE®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, TIXOGEL®, and VISCOSEAL® are registered trademarks of BYK Additives. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAC®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents. This issue replaces all previous versions – Printed in the USA