

DISPERBYK-193

Wetting and dispersing additive for aqueous printing inks. Particularly recommended for binder-containing pigment concentrates.

Product Data

Composition

Solution of a copolymer with pigment-affinic groups

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (68 °F):	8.76 lbs/US gal
Non-volatile matter (10 min., 302 °F):	40 %
Solvents:	Water

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

To be stored and transported at a temperature below 40 °C (104 °F). Separation or turbidity may occur. Mix well before use. Do not exceed 50 °C (122 °F).

Special Note

The appearance of DISPERBYK-193 varies between clear and opaque. This does affect the performance of the product and is not part of the specification.

Applications

Printing Inks

Special Features and Benefits

The additive deflocculates pigments by means of steric stabilization. As a result of the small particle size of the deflocculated pigments, high levels of gloss can be achieved and the color strength, transparency, and storage stability are improved. The millbase viscosity is greatly reduced even with a low dosage of DISPERBYK-193. This makes it possible to produce highly filled pigment concentrates with good flow properties.

DISPERBYK-193

Data Sheet
Issue 04/2014

Recommended Use

DISPERBYK-193 is particularly recommended for the production of binder-containing pigment concentrates that are used in aqueous gravure, flexographic and screen printing inks. The amounts required are low and facilitates the production of cost-effective, highly filled pigment concentrates with good flow properties. The additive reduces the tendency to foam which is often observed when using grinding resins, and it improves the colorant acceptance. As a defoamer in the millbase, the combination of BYK-012 and BYK-017 (1:1) has proven to be very effective (dosage 0.6 % based on the total formulation).

Recommended Levels

Amount of additive (as supplied) based upon pigment:

Titanium dioxides: 1-3 %
Organic pigments: 4-6 %
Carbon blacks: 4-6 %

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

For optimum performance, the additive should be added slowly (whilst stirring) to the grinding resin or to the shear-stable dispersion. Only add the pigments once the additive has been uniformly distributed.



Additive Guide



BYK USA Inc.
524 South Cherry Street
P.O. Box 5670
Wallingford, CT 06492
USA
Tel 203 265-2086
Fax 203 284-9158

cs.usa@byk.com
www.byk.com

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABEN®, BENTOLITE®, CLAYTONE®, CLOISITE®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, TIXOGEL®, and VISCOSEAL® are registered trademarks of BYK Additives. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAC®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents. This issue replaces all previous versions – Printed in the USA