

BYK-1790

Silicone-free, polymer-based defoamer for solvent-free, radiation-curing wood and industrial coatings, printing inks and adhesives. Suitable for pigmented and unpigmented coating systems.

Product Data

Composition

Mixture of foam-destroying polymers, silicone-free

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (68 °F): 7.06 lbs/US gal
Non-volatile matter (10 min., 302 °F): 100 %

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Applications

Coatings and Printing Inks

Special Features and Benefits

BYK-1790 is silicon-free and is recommended for solvent-free, radiation-curing (UV and ESH) coating systems (pigmented and unpigmented), printing inks and overprint varnishes. The high efficiency of the defoamer is not impacted by pigments, fillers, wax additives or matting agents.

Recommended Levels

0.1-0.7 % additive (as supplied) based upon the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

Due to its high incompatibility, the defoamer must be incorporated at high shear forces (in the mill base) to ensure good distribution. Otherwise defects may occur in the system.

BYK-1790

Data Sheet
Issue 04/2013

Adhesives & Sealants

Special Features and Benefits

BYK-1790 is silicon-free and is recommended for solvent-free, radiation-curing (UV and ESH) adhesives (pigmented and unpigmented) as well as for reactive polyurethane hot melt adhesives. It has no negative effect on the adhesive properties of the adhesives. In radiation curing formulations, BYK-1790 is ideal for universal use in acrylate based binders. It prevents foaming in the manufacture of reactive polyurethane hot melt adhesives even at high viscosity. Significantly shorter evacuation times lead to an increase in the efficiency of production due to the additive.

Recommended Levels

0.1-0.7 % additive as supplied based on the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

Due to its high incompatibility, the defoamer must be incorporated at high shear forces (in the mill base) to ensure good distribution. Otherwise defects may occur in the system.

BYK USA Inc.
524 South Cherry Street
P.O. Box 5670
Wallingford, CT 06492
USA
Tel 203 265-2086
Fax 203 284-9158

cs.usa@byk.com
www.byk.com/additives

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.

This issue replaces all previous versions – Printed in the USA