

## BYK-349

Silicone surfactant for aqueous coatings, adhesives and maintenance products with a considerable reduction in the surface tension and therefore good substrate wetting. Does not increase the surface slip. Suitable for systems that do not contain co-solvents. All-purpose.

### Product Data

#### Composition

Polyether-modified siloxane

#### Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Active substance: 100 %

Density (68 °F): 8.65 lbs/US gal

#### Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit [www.byk.com](http://www.byk.com) for further information.

#### Special Note

The additive has long-term stability in the pH range 4-10. It is also suitable for systems that do not contain organic co-solvents. If the system contains increased quantities of co-solvents, the silicone surfactant will not be as effective. In such formulations, we recommend the use of a polysiloxane, e.g. BYK-333.

### Applications

#### Coatings Industry

##### Special Features and Benefits

The additive produces a significant decrease in the surface tension in aqueous coatings and therefore particularly improves substrate wetting and leveling. It only marginally, if at all, stabilizes foam and the recoatability is not impaired. The additive does not increase the surface slip. If a greater surface slip is required, we recommend that it is combined with a polysiloxane such as BYK-333.

**Recommended Use**

|                             |                                     |
|-----------------------------|-------------------------------------|
| Automotive coatings         | <input checked="" type="checkbox"/> |
| Architectural coatings      | <input checked="" type="checkbox"/> |
| Wood and furniture coatings | <input checked="" type="checkbox"/> |
| Industrial coatings         | <input checked="" type="checkbox"/> |
| Can coatings                | <input checked="" type="checkbox"/> |
| Coil coatings               | <input checked="" type="checkbox"/> |
| Protective systems          | <input checked="" type="checkbox"/> |
| Leather finishes            | <input type="checkbox"/>            |

Particularly recommended     Recommended

The additive is especially recommended for all aqueous coatings that do not contain co-solvents, particularly those based on styrene-acrylic, pure acrylate, acrylate/polyurethane combinations, polyurethanes, and also for baking systems.

**Recommended Levels**

0.05-0.5 % additive (as supplied) based upon total formulation.

The above recommended levels can be used for orientation. Optimal dosage levels are determined through a series of laboratory tests.

**Incorporation and Processing Instructions**

It is preferable to add the additive to the finished coating. However, it can be used at any stage during the coating manufacture.

**Adhesives & Sealants**

**Special Features and Benefits**

BYK-349 is a highly effective silicone surfactant. The additive causes a considerable reduction in the surface tension in aqueous adhesive systems. It thereby improves the wetting of critical substrates.

**Recommended Levels**

0.05-0.5 % additive (as supplied) based upon total formulation.

The above recommended levels can be used for orientation. Optimal dosage levels are determined through a series of laboratory tests.

**Incorporation and Processing Instructions**

It is preferable to add the additive to the finished formulation. However, it can be used at any stage during manufacture.

## Care Products and Polishes

### Special Features and Benefits

BYK-349 is a highly effective silicone surfactant with a considerable reduction in the surface tension to improve the substrate wetting and leveling in aqueous maintenance products. It only marginally, if at all, stabilizes the foam, does not impair the subsequent layer and does not increase the surface slip.

### Recommended Use

The additive is particularly recommended for plasticizer-free floor care products and wax cleaning agents.

### Recommended Levels

0.05-0.5 % additive (as supplied) based upon total formulation.

The above recommended levels can be used for orientation. Optimal dosage levels are determined through a series of laboratory tests.

### Incorporation and Processing Instructions

It is preferable to add the additive to the already completed formulation. However, it can be used at any stage during the coating manufacture.

## BYK-349

Data Sheet  
Issue 04/2013

**BYK USA Inc.**  
524 South Cherry Street  
P.O. Box 5670  
Wallingford, CT 06492  
USA  
Tel 203 265-2086  
Fax 203 284-9158

**cs.usa@byk.com**  
**www.byk.com/additives**

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYPK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.

This issue replaces all previous versions – Printed in the USA