

BYK-364 P

Polyacrylate-based powdered surface additive for powder coatings.
Polar anti-cratering and leveling additive to support pigment and substrate wetting.

Product Data

Composition

Polyacrylate, adsorbed on silicon dioxide

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Acrylate content:	60 %
Density (68 °F):	11.02 lbs/US gal
Residue after calcining:	37 %
Supplied as:	Powder

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Applications

Powder Coatings

Special Features and Benefits

BYK-364 P is an effective anti-cratering additive. It reduces the orange peel effect by optimizing the leveling properties of the powder coating. Pinholes, fish eyes and other surface defects are prevented. The polar structure of the additive improves pigment wetting and substrate wetting. A better DOI value (distinctness of image) and a surface with fewer pinholes is achieved, especially in TGIC-alternative powder coating systems. BYK-364 P is an OH-reactive additive which can be integrated in the polymer compound by reacting with suitable binders.

Recommended Use

The additive is recommended for powder coatings based on epoxy, polyester, polyurethane and acrylate resins and polyester/epoxy combinations.

Recommended Levels

0.5-2 % additive (as supplied) based upon total formation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive is mixed with resin, hardener, pigments and other raw materials in a high-speed mixer and then extruded. Good dispersion of the additive by the extruder promotes gloss and leveling of the powder coating and prevents the formation of craters, fish eyes and seeds.

BYK-364 P

Data Sheet
Issue 12/2012

BYK USA Inc.
524 South Cherry Street
P.O. Box 5670
Wallingford, CT 06492
USA
Tel 203 265-2086
Fax 203 284-9158

cs.usa@byk.com
www.byk.com/additives

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.

This issue replaces all previous versions – Printed in the USA