

BYK-UV 3570

Crosslinking, silicone-containing surface additive for radiation-curable coatings to reduce the surface tension and increase the surface slip.

Product Data

Composition

Solution of polyester-modified, multi-acrylic functional polydimethylsiloxane

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (68 °F):	8.93 lbs/US gal
Refractive index (68 °F):	1.465
Active substance:	70 %
Solvents:	Propoxylated neopentyl glycol diacrylate (PONPGDA)
Flash point:	144 °F

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

To be stored and transported at a temperature below 35 °C (95 °F).

Applications

Coatings Industry

Special Features and Benefits

Due to its high surface activity, BYK-UV 3570 orientates itself at the surface of the coating. Its acrylic functionality enables it to be incorporated in the polymer network and anchored there. Depending on the dosage, the additive provides a controlled increase in the surface slip, therefore enabling the required slip to be adjusted more easily. BYK-UV 3570 also improves the leveling, the substrate wetting and the orientation of matting agents. If the additive is fixed to the coating surface via its reactive groups, these properties are maintained for a long period of time.

Recommended Use

BYK-UV 3570 is particularly recommended for all solvent-free, radiation-curable coatings.

BYK-UV 3570

Data Sheet
Issue 06/2013

Recommended Levels

0.1-3 % additive (as supplied) based upon total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive can be incorporated during any stage of the production process, including post-addition.



Additive Guide



BYK USA Inc.
524 South Cherry Street
P.O. Box 5670
Wallingford, CT 06492
USA
Tel 203 265-2086
Fax 203 284-9158

cs.usa@byk.com
www.byk.com/additives

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.

This issue replaces all previous versions – Printed in the USA