

# CERAFAK 140 N

Dispersion of a carnauba wax for solvent-borne can coatings, to improve the surface slip and the scratch resistance.

## Product Data

### Composition

Carnauba wax dispersion

### Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Non-volatile matter: 15 %  
Carrier: Isobutanol/naphthalene-depleted aromatic hydrocarbons 13/4  
Melting point (wax content): 185 °F  
Viscosity (73 °F, D=400/s): 30 mPa·s

### Food Contact Legal Status

The additive is suitable for applications in direct food contact. For the current food contact legal status, please contact our product safety department or visit [www.byk.com](http://www.byk.com) for further information.

### Storage and Transportation

Temperature sensitive. To be stored and transported at a temperature below 35 °C (95 °F).  
Stir before use.

## Applications

### Coatings Industry

#### Special Features and Benefits

The additive increases the surface slip in solvent-borne can coatings and simultaneously improves the scratch resistance.

#### Recommended Levels

1.3-6 % additive (as supplied) based upon total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

#### Incorporation and Processing Instructions

The additive is preferably incorporated into the coating at the end of the production process with a low shear rate. Mix well before use.

# CERAFAK 140 N

Data Sheet  
Issue 08/2013



Additive Guide



**BYK USA Inc.**  
524 South Cherry Street  
P.O. Box 5670  
Wallingford, CT 06492  
USA  
Tel 203 265-2086  
Fax 203 284-9158

[cs.usa@byk.com](mailto:cs.usa@byk.com)  
[www.byk.com/additives](http://www.byk.com/additives)

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.

This issue replaces all previous versions – Printed in the USA