

# CERAFLOUR 962

Highly effective wax additive for improved degassing of powder coatings on porous substrates.

## Product Data

### Composition

Micronized, modified polyethylene wax

### Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density:	8.35 lbs/US gal
Melting point:	284 °F
Particle size distribution (laser diffraction, volume distribution):	D50: 9 µm      D90: 21 µm
Supplied as:	Micropowder

### Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit [www.byk.com](http://www.byk.com) for further information.

### Storage and Transportation

Temperature sensitive. To be stored and transported at a temperature below 50 °C (122 °F).

## Applications

### Powder Coatings

#### Special Features and Benefits

The additive improves the degassing of powder coatings, which are applied to porous substrates. It reduces the formation of pinholes and air bubbles and optimizes the scratch resistance.

#### Recommended Use

CERAFLOUR 962 is used in powder coatings based on polyester/TGIC/Beta-HAA/epoxy-functional glycidyl esters, polyester/epoxy, polyurethane, acrylate, and epoxy.

#### Recommended Levels

0.5-2 % additive (as supplied) based on the total formulation when extruding with all formulation components.

0.5-4 % additive (as supplied) based on the total formulation with post-addition to the powder coating.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

## CERAFLOUR 962

Data Sheet  
Issue 01/2014

### Incorporation and Processing Instructions

The product should be mixed with the resin, hardener, pigments and other additives using a high speed mixer and extruded along with all components. As it is a free-flowing product, CERAFLOUR 962 can also be added as a post additive. With sufficiently thorough mixing, it can be added to the finished powder coating without leading to seeding.



Additive Guide



**BYK USA Inc.**  
524 South Cherry Street  
P.O. Box 5670  
Wallingford, CT 06492  
USA  
Tel 203 265-2086  
Fax 203 284-9158

[cs.usa@byk.com](mailto:cs.usa@byk.com)  
[www.byk.com](http://www.byk.com)

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABEN®, BENTOLITE®, CLAYTONE®, CLOISITE®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, TIXOGEL®, and VISCOSEAL® are registered trademarks of BYK Additives. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents. This issue replaces all previous versions – Printed in the USA