

CERAFLOUR 965

Micronized PTFE for powder coatings. Creates fine-textured, scratch-resistant and matte surfaces.

Product Data

Composition

Micronized PTFE

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Particle size distribution (laser diffraction, volume distribution): D50: 31 µm D90: 80 µm
Supplied as: Micropowder

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Temperature sensitive. To be stored and transported at a temperature below 50 °C (122 °F).

Applications

Powder Coatings

Special Features and Benefits

The additive creates highly reproducible fine-textured, matte and scratch-resistant surfaces in all common powder coating systems. The obtained textures are uniform, even if the layer thickness is variable.

Recommended Levels

0.1-0.4 % additive (as supplied) based upon total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive is mixed with resin, hardener, pigments and other additives in a high-speed mixer and then extruded together with all components.

CERAFLOUR 965

Data Sheet
Issue 08/2013



Additive Guide



BYK USA Inc.
524 South Cherry Street
P.O. Box 5670
Wallingford, CT 06492
USA
Tel 203 265-2086
Fax 203 284-9158

cs.usa@byk.com
www.byk.com/additives

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.

This issue replaces all previous versions – Printed in the USA