

# CERAFLOUR 967

Synthetic polymer for powder coatings to obtain coarse-textured surfaces. In conjunction with metal pigments, uniform hammertone and antique surfaces can be achieved.

## Product Data

### Composition

Synthetic polymer

### Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Particle size: < 1000 µm  
Density (DIN 53127): 1.11 g/ml  
Supplied as: Powder

### Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit [www.byk.com](http://www.byk.com) for further information.

### Storage and Transportation

Temperature sensitive. To be stored and transported at a temperature below 50 °C (122 °F).

## Applications

### Powder Coatings

#### Special Features and Benefits

The additive is used to obtain coarse-textured powder coating surfaces. It is very compatible and provides homogenous and highly reproducible textural effects. Adding metal pigments creates uniform hammertone and antique surfaces. Excellent separation of the metal pigments is achieved in this system.

#### Recommended Levels

0.1-0.3 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

#### Incorporation and Processing Instructions

The additive is mixed with resin, hardener, pigments and other additives in a high-speed mixer and then extruded together with all components.

#### Special Note

The creation of texture with CERAFLOUR 967 is only possible when not using a leveling agent at the same time. When using leveling additives at the same time, a non-textured surface with craters is the result.

# CERAFLOUR 967

Data Sheet  
Issue 03/2014



Additive Guide



**BYK USA Inc.**  
524 South Cherry Street  
P.O. Box 5670  
Wallingford, CT 06492  
USA  
Tel 203 265-2086  
Fax 203 284-9158

**cs.usa@byk.com**  
**www.byk.com/additives**

ACTAL®, ADJUST®, ADVITROL®, ALUFERSOL®, ANTI-TERRA®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CLAYTONE®, CLOISITE®, COPISIL®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, FULGEL®, FULMONT®, GARAMITE®, GELWHITE®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, SILBYK®, TIXOGEL®, VISCOBYK®, Y-25®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.

This issue replaces all previous versions – Printed in the USA