

## LG Chemical LUPOL HI4352L PP+Rubber+MF, High Impact

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Mineral Reinforced, Impact Modified

### Material Notes:

Description: Injection Molding, PP+Rubber+MF, Good Dimensional Stability, High Impact  
 Application: Automotive Exterior (Sill Side Molding, Door Garnish)  
 CAS: 9003-07-0, 26221-73-8 and 14807-96-6  
 Information provided by LG Chemical

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_LG-Chemical-LUPOL-HI4352L-PPRubberMF-High-Impact.php](http://www.lookpolymers.com/polymer_LG-Chemical-LUPOL-HI4352L-PPRubberMF-High-Impact.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.09 g/cc	1.09 g/cc	ASTM D792
Maximum Moisture Content	0.010	0.010	Injection Molding
Melt Flow	20 g/10 min @Load 2.16 kg, Temperature 230 Å°C	20 g/10 min @Load 4.76 lb, Temperature 446 Å°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	16.7 MPa @Thickness 3.20 mm	2420 psi @Thickness 0.126 in	50mm/min; ASTM D638
Elongation at Break	150 % @Thickness 3.20 mm	150 % @Thickness 0.126 in	50mm/min; ASTM D638
Flexural Yield Strength	25.5 MPa @Thickness 6.40 mm	3700 psi @Thickness 0.252 in	10mm/min; ASTM D790
Flexural Modulus	1.65 GPa @Thickness 6.40 mm	239 ksi @Thickness 0.252 in	10mm/min; ASTM D790
Izod Impact, Notched	>= 0.490 J/cm @Thickness 6.40 mm, Temperature -30.0 Å°C	>= 0.918 ft-lb/in @Thickness 0.252 in, Temperature -22.0 Å°F	ASTM D256
	>= 3.92 J/cm @Thickness 6.40 mm, Temperature 23.0 Å°C	>= 7.35 ft-lb/in @Thickness 0.252 in, Temperature 73.4 Å°F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	120 Å°C @Thickness 3.20 mm	248 Å°F @Thickness 0.126 in	Unannealed; ASTM D648

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	190 - 210 Â°C	374 - 410 Â°F	Injection Molding
Middle Barrel Temperature	200 - 230 Â°C	392 - 446 Â°F	Injection Molding
Front Barrel Temperature	200 - 230 Â°C	392 - 446 Â°F	Injection Molding
Nozzle Temperature	210 - 230 Â°C	410 - 446 Â°F	Injection Molding
Melt Temperature	200 - 230 Â°C	392 - 446 Â°F	Injection Molding
Mold Temperature	40.0 - 60.0 Â°C	104 - 140 Â°F	Injection Molding
Drying Temperature	70.0 - 80.0 Â°C	158 - 176 Â°F	Injection Molding
Dry Time	3.00 - 4.00 hour	3.00 - 4.00 hour	Injection Molding
Back Pressure	29.4 - 58.8 MPa	4260 - 8530 psi	Injection Molding
Screw Speed	30 - 60 rpm	30 - 60 rpm	Injection Molding

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China