

Razin™ Engineering Plastics		Quality Management System Product Information	
Form Code:7Te02F1	No.:A111U		

Razamid® A111U

Razamid A111U is an Injection grade Impact modified natural color polyamide 66. It combines good strength, stiffness and toughness as well as excellent heat, chemical and abrasion resistance.

Properties	Test Method	Unit	Value
Physical			
Density	ASTM D 792	g/cm ³	1.13
Linear Mold Shrinkage	ASTM D 955	%	0.8

Mechanical			
Tensile Strength, Yield	ASTM D 638	MPa	45
Elongation at Break	ASTM D 638	%	50
Flexural Strength	ASTM D 790	MPa	65
Flexural Modulus	ASTM D 790	MPa	1800
Izod Impact, Notched @ 23 °C	ASTM D 256	KJ/m ²	Not break
@ -30 °C			

Thermal			
Melting Point	ASTM D 3418	°C	250
Deflection Temperature Under Load @ 0.46 MPa	ASTM D 648		215
@ 1.8 MPa		°C	80
Vicat Softening point	ASTM D 1525	°C	225

Electrical			
Surface Resistivity	IEC 60093	Ohm	10 ¹²
Volume Resistivity	IEC 60093	Ohm.cm	10 ¹³
Dielectric constant	ASTM D 150		
Dielectric strength	ASTM D 149	KV/mm	20

Processing						
Drying:						
	Drying Time:	2.0 – 4.0 hr		Drying Temperature:	90 - 110 °C	
Injection Molding:						
Item	Rear Temp (°C)	Middle Temp (°C)	Front Temp (°C)	Melt Temp (°C)	Mold Temp (°C)	Inj. Pressure (Mpa)
Min	260	265	275	275	50	55
Max	280	300	305	310	80	140

The data contained in this publication are based on our current knowledge and experience. In view of the many actors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose.

Razin™ Engineering Plastics

Sales Office: Unit1, No.332, Mokhberi Blvd, North janat abad St., Tehran,Iran

Tel: + (98) 21 44623931

Fax: +(98) 21 44623931

Web address: www.Razinpolymer.com