

BYK-W 980

Wetting and dispersing additive to reduce viscosity and prevent fillers from settling in ambient curing resin systems and adhesives as well as for polyester molding compounds, wet mat molding and pultrusion applications

Product Data

Composition

Solution of a salt of unsaturated polyamine amides and acidic polyesters

Percentage of renewable raw materials: 52 %

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Amine value:	30 mg KOH/g
Acid value:	40 mg KOH/g
Density (68 °F):	8.26 lbs/US gal
Non-volatile matter (10 min., 302 °F):	80 %
Flash point:	151 °F

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Mix well before use. Separation or turbidity possible. Warm to 30-60 °C (86-140 °F) and mix well.

Applications

Ambient Curing Systems

Special Features and Benefits

The wetting and dispersing additive improves the dispersion of all conventional fillers, such as calcium carbonate and aluminum hydroxide. It reduces the viscosity of the filled resin, allowing a higher filling level. In most cases, the settling of fillers during storage and processing is reduced.

Recommended Use

The additive is especially recommended for unsaturated polyester resins as well as acrylic, polyurethane and epoxy resins, and is highly effective in all areas of application.

Recommended Levels

0.5-1.5 % additive (as supplied) based upon fillers.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

For optimal performance, the additive should be incorporated before solids are added.

BYK-W 980

Data Sheet
Issue 09/2012

Adhesives & Sealants

Special Features and Benefits

The additive improves the wetting and dispersion of all mineral fillers, such as calcium carbonate and aluminum hydroxide (ATH), which lowers viscosity and allows higher filling levels. At the same time, the sedimentation of fillers is often reduced, preventing deposits. In many cases, the additive is more effective than BYK-W 966.

Recommended Use

The additive is particularly recommended for adhesives on the basis of polyurethane, epoxy and acrylic resins.

Recommended Levels

0.5-1.5 % additive (as supplied) based upon fillers.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

For optimal performance, the additive should be incorporated before solids are added.

SMC, Wet Mat Molding and Pultrusion

Special Features and Benefits

The additive improves the wetting and dispersion of fillers in wet mat molding and HMC polyester molding compounds. This lowers the viscosity, allows higher filling levels and improves glass fiber wetting. In pultrusion applications, the additive improves the wetting and dispersion of fillers, prevents the fillers from settling in the impregnation bath, and improves glass fiber wetting through lowered viscosity.

Recommended Use

The additive is particularly recommended for HMC polyester molding compounds, wet mat molding and pultrusion applications on the basis of UP/VE, epoxy and acrylic resins.

Recommended Levels

1-2 % additive (as supplied) based upon fillers for HMC molding compounds and wet mat molding.
0.5-1.5 % additive (as supplied) based upon fillers for pultrusion applications.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

For optimal performance, the additive should be incorporated before solids are added.

BYK USA Inc.
524 South Cherry Street
P.O. Box 5670
Wallingford, CT 06492
USA
Tel 203 265-2086
Fax 203 284-9158

cs.usa@byk.com
www.byk.com/additives

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.

This issue replaces all previous versions – Printed in the USA