

Data Sheet Issue 04/2016

# **BYK-W 961**

Wetting and dispersing additive against settling in ambient curing resin systems. Specifically for mineral-filled PU systems.

## **Product Data**

### Composition

Solution of an alkyl ammonium salt of polycarboxylic acid

### **Typical Properties**

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

| Amine value:      | 60 mg KOH/g      |
|-------------------|------------------|
|                   | 5 5              |
| Acid value:       | 60 mg KOH/g      |
| Density (68 °F):  | 7.96 lbs/US gal  |
| Solvents:         | Propylene glycol |
| Flash point:      | 226 °F           |
| Active substance: | 100 %            |
|                   |                  |

### **Food Contact Legal Status**

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

### Storage and Transportation

Separation or turbidity may occur at temperatures below 10 °C (50 °F).

## **Applications**

### **Ambient Curing Resin Systems**

#### **Special Features and Benefits**

BYK-W 961 is an anti-settling additive. It is especially recommended for mineral-filled polyurethane systems. Propylene glycol is used as a solvent for the active substance and cross-links with isocyanate when curing.

#### **Recommended Levels**

0.5-1.5 % additive (as supplied) based on the filler.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

### **Incorporation and Processing Instructions**

For optimum performance, the additive should be added before the solids.

Data Sheet Issue 04/2016

#### **Adhesives & Sealants**

#### **Special Features and Benefits**

BYK-W 961 is an anti-settling additive. It is especially recommended for mineral-filled polyurethane systems. Propylene glycol is used as a solvent for the active substance and cross-links with isocyanate when curing.

#### **Recommended Levels**

0.5-1.5 % additive (as supplied) based on the filler.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

#### **Incorporation and Processing Instructions**

For optimum performance, the additive should be added before the solids.







#### BYK USA Inc.

524 South Cherry Street P.O. Box 5670 Wallingford, CT 06492 USA Tel 203 265-2086 Fax 203 284-9158

cs.usa@byk.com www.byk.com

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKUPT®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SCONA®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABEN®, BENTOLITE®, CLAYTONE®, CLOIST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RIC-SYN®, TIXOGEL®, and VISCOSEAL® are registered trademarks of BYK Additives. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® regregationed trademarks of BYK

are registered trademarks of BYK-Cera.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents. This issue replaces all previous versions - Printed in the USA