

Product information

# Dynasylan<sup>®</sup> 4148

# Polyethyleneglycol-functional alkoxysilane

## **Technical data**

Properties and test methods	Value	Unit	Method
Viscosity (20 °C)	10 - 20	mPa.s	DIN 53015
Freezing point	< - 10	°C	DIN ISO 3016
Density (20 °C)	арргох. 1.1	g/cm³	DIN 51757
Flash point	> 95	°C	EN 22719

## Registrations

Dynasylan® 4148	
AICS (Australia):	No
DSL/NDSL (Canada):	Yes
PICCS (Philippines):	Yes
TSCA (USA):	Yes
IECSC (P.R. China):	Yes
ENCS (Japan):	Yes
ECL (South Korea):	Yes
EINECS/ELINCS (EU):	Yes

**Dynasylan**<sup>\*</sup> 4148 is a ready-for-use silane and is soluble in water and most organic solvents.

**Dynasylan**<sup>\*</sup> 4148 helps to control rheological properties and to reduce viscosity in highly-filled polymer systems, like aluminum trihydroxide-filled polyesters or SMC-pastes.

Contrary to most other organofunctional silanes, **Dynasylan**\* 4148 features chemical polarity yet remaining chemically not reactive. Such a product is used as a hydrophilic compatibilizer rather than a covalent adhesion promoter.

**Dynasylan**<sup>\*</sup> 4148 permits workable viscosities at well over 250 phr aluminum trihydroxide loading in unsaturated polyester resins. Further more, **Dynasylan**<sup>\*</sup> 4148 can be used as antisettling agent for corrosion inhibitors in glycol based cooling agents.

As a non-coupling silane **Dynasylan**<sup>•</sup> 4148 can also be used as a slipping agent to simply modify a surface.

# Safety and handling

Before considering the use of Dynasylan® products please read its Material Safety Data sheet (MSDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use. The Material Safety Data Sheet is available after registration on our website www.dynasylan.com or upon request from your local representative, customer service or from Evonik Industries AG, Product Safety Department, E-MAIL sds-im@evonik.com.

# Packaging and storage

**Dynasylan**<sup>®</sup> 4148 is supplied in pails with a capacity of 25 kg and drums with 200 kg. The containers must remain tightly sealed during storage and kept in a well aired place. Protection against humidity is essential. In the unopened container **Dynasylan**<sup>®</sup> 4148 has a shelf life of least one year.

## **Properties and application**

**Dynasylan**<sup>®</sup> 4148 can be added neatly to a blend of filler or pigment and resin, or it can be used for the pretreatment of the filler or pigment.

Pre-treatment of the filler or pigment is best achieved in a highspeed mixer by spraying **Dynasylan**<sup>®</sup> 4148 into a well-agitated filler or pigment bed. In order to obtain maximum efficiency of the treated filler or pigment, a good distribution of **Dynasylan**<sup>®</sup> 4148 throughout the filler or pigment surface is essential.

If the surface area of a filler or pigment is unknown, 1 percent by weight of **Dynasylan**<sup>®</sup> 4148, based on filler or pigment, is a convenient initial basis for Pre-treatment. Subsequently, the exact **Dynasylan**<sup>®</sup> 4148 loading should be determined empirically.

Moreover, **Dynasylan**<sup>\*</sup> 4148 can act as a lubricant and wetting agent in the glass fibre industry in combination with silane coupling agents.

As a non-coupling silane, **Dynasylan**<sup>®</sup> 4148 can dramatically reduce the dispersion viscosity of aluminum trihydroxide and many other fillers and pigments. Because of better wetting and dispersion, outstanding filler or pigment loadings at a given viscosity can be realized with **Dynasylan**<sup>®</sup> 4148.

**Dynasylan**<sup>\*</sup> 4148 helps to increase pigment dispersion predominantly in aqueous media, thus leading to an enhanced gloss of a typical coating.

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. EVONIK DISCLAIMS ALL REPRESENTATIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, AND SHALL HAVE NO LIABILITY FOR, MERCHANTABILITY OF THE PRODUCT OR ITS FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE), OR OTHERWISE. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used.

#### Europe/Middle-East/Africa/RoW Evonik Industries AG

Inorganic Materials Rodenbacher Chaussee 4 63457 Hanau-Wolfgang Germany PHONE +49 6181 59 13636 FAX +49 6181 59 13737 dynasylan@evonik.com www.dynasylan.com

#### Asia / Pacific Evonik Degussa (SEA) Pte. Ltd.

Inorganic Materials 3 Internatioanl Business Park #07-18, Nordic European Centre Singapore 609927 PHONE +65 6809 6830 FAX +65 6809 6630 dynasylan@evonik.com www.dynasylan.com

### Asia / Pacific

Evonik Taiwan Ltd. Inorganic Materials Artist Construction Bldg. 9F, No. 133 Min Sheng East Road, Sec 3 Taipei, 105 Taiwan, R.O.C. Taiwan PHONE +886 227 17 1242 FAX +886 227 17 2106 dynasylan@evonik.com

#### North America Evonik Degussa Corporation

Inorganic Materials P.O. Box 677 299 Jefferson Road Parsippany, NJ 07054-0677 USA PHONE (TOLL FREE) +1 800 237 67 45 PHONE +1 973 929 8513 FAX +1 973 929 8503 dynasylan@evonik.com www.dynasylan.com

#### Asia / Pacific Evonik Degussa (Shanghai) Co. Ltd.

Inorganic Materials 55, Chungdong Road Shanghai 201108 P.R. China PHONE +86 21 6119 1053 FAX +86 21 6119 1075 dynasylan@evonik.com www.dynasylan.com

# Asia / Pacific

Evonik Japan Co. Ltd

Inorganic Materials 12th Floor Monolith Building 2-3-1, Nishi-Shinjuku-ku Tokyo 163-0912 Japan PHONE +81 353 23 7300 FAX +81 353 23 7399 dynasylan@evonik.com www.dynasylan.com

#### Latin America Evonik Brasil Ltda.

Inorganic Materials Alameda Campinas, 579 01404-000 São Paulo-SP Brazil PHONE +55 11 3146 4123 FAX +55 11 3146 4109 dynasylan@evonik.com www.dynasylan.com

# Asia / Pacific

Evonik Korea Ltd.

Inorganic Materials 94, Galsan 1-dong Bupyeong-gu Incheon, 403-081 Korea PHONE +82 32 510 2433 FAX +82 32 505 2510 dynasylan@evonik.com www.dynasylan.com

#### Asia / Pacific

Evonik India Pvt. Ltd. Inorganic Materials Krislon House Saki Vihar Road, Anderi (E) Mumbai - 400 072 India PHONE +91 226 7238 800 FAX +91 226 7238 811 dynasylan@evonik.com www.dynasylan.com

