

Product information

Dynasylan® DAMO-T

N-(2-Aminoethyl)-3-aminopropyltrimethoxysilane

Technical data

Properties and test methods	Value	Unit	Method
Refractive index n (20,D)	арргох. 1.444	-	DIN 51423
Flash point	арргох. 90/ 194	°C/ °F	DIN 51423
Viscosity (25 °C/ 68 °F)	арргох. 7/ 6.8	mPa·s / cSt	DIN 53015
Density (20 °C/ 68 ° F)	арргох. 1.03	g/cm ³	DIN 51757

Registrations

Dynasylan® DAMO-T

EINECS/ELINCS (EU):	Yes
AICS (Australia):	Yes
DSL/NDSL (Canada):	Yes
PICCS (Philippines):	Yes
TSCA (USA):	Yes
IECS (P.R. China):	Yes
ENCS (Japan):	Yes
ECL (South Korea):	Yes

Dynasylan DAMO-T is a bifunctional organosilane possessing two reactive amino groups and hydrolyzable inorganic methoxysilyl groups.

The dual nature of its reactivity allows **Dynasylan*** DAMO-T to bind chemically to both inorganic materials (e.g. glass, metals, fillers) and organic polymers (e.g. thermosets, thermoplastics, elastomers), thus functioning as an adhesion promoter and surface modifier.

Dynasylan* DAMO-T is a yellow liquid with an amine-like odor. It is soluble in alcohols, and aliphatic or aromatic hydrocarbons.

Safety and handling

Before considering the use of Dynasylan® and Protectosil® products please read its Material Safety Data sheet (MSDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use. The Material Safety Data Sheet is available after registration on our website www.dynasylan.com or upon request from your local representative, customer service or from Evonik Industries AG, Product Safety Department, E-MAIL sds-im@evonik.com.

Packaging and storage

Dynasylan° DAMO-T is supplied in 25 kg and 200 kg drums and 950 kg containers. In the unopened container **Dynasylan**° DAMO-T has a shelf life of at least one year.

Properties and application

Dynasylan* DAMO-T is an important additive in applications such as:

- glass fibre/glass fabric composites: as a finish or size constituent
- glass and metal primers
- foundry resins: as an additive to various types of foundry resins
- sealants and adhesives: as a primer or additive
- mineral-filled polymers (composites): for pretreatment of fillers and pigments or as an additive
- paints and coatings: as an additive and/or primer for improving adhesion to the substrate.

The most important effects which can be achieved through the use of **Dynasylan*** DAMO-T are:

improved product properties, such as

- flexural strength, tensile strength, impact strength and modulus of elasticity
- moisture and corrosion resistance

improved in processing properties, such as

adhesion

Reactivity

In the presence of water the methoxy groups of <code>Dynasylan*</code> DAMO-T hydrolyze to form reactive silanol groups which can bond to a variety of inorganic substrates. The organophilic diamino group of <code>Dynasylan*</code> DAMO-T can react with a suitable polymer.

The hydrolysis of **Dynasylan**® DAMO-T takes place autocatalytically. The pH value of the hydrolysate is about 10-11. For a longer stability of the hydrolysate a pH of 4 is recommended. Examples of suitable inorganic substrates are glass or glass fibers.

Dynasylan* DAMO-T may be used with such polymers as phenolic, furan resins, PA, PBT, PC, EVA, modified PP, PVAC, PVC, acrylates and silicones.

Dynasylan® DAMO-T can undergo reactions with ketone or ester solvents. The silane or silanized substrates can react with carbon dioxide to form the corresponding carbonates and/or carbamates.

Processing

For substrate pretreatments (e.g. as a primer) **Dynasylan®** DAMO-T may be used as an approximately 0.5-2 wt.-% solution in an organic solvent such as alcohol, as a constituent of aqueous sizes or solutions, neat, or added to the polymer as an additive (at higher concentration: 1-10 wt.-%).

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. EVONIK DISCLAIMS ALL REPRESENTATIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, AND SHALL HAVE NO LIABILITY FOR, MERCHANTABILITY OF THE PRODUCT OR ITS FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE), OR OTHERWISE. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used.

Europe/Middle-East/Africa/RoW Evonik Industries AG

Inorganic Materials Rodenbacher Chaussee 4 63457 Hanau-Wolfgang Germany PHONE +49 6181 59 13636 FAX +49 6181 59 13737 dynasylan@evonik.com www.dynasylan.com

Asia / Pacific Evonik Degussa (SEA) Pte. Ltd.

Inorganic Materials 3 Internatioanl Business Park #07-18, Nordic European Centre Singapore 609927 PHONE +65 6809 6830 FAX +65 6809 6630 dynasylan@evonik.com www.dynasylan.com

Asia / Pacific Evonik Taiwan Ltd.

Inorganic Materials Artist Construction Bldg. 9F, No. 133 Min Sheng East Road, Sec 3 Taipei, 105 Taiwan, R.O.C. Taiwan PHONE +886 227 17 1242 FAX +886 227 17 2106 dynasylan@evonik.com www.dynasylan.com

North America Evonik Degussa Corporation

Inorganic Materials
P.O. Box 677
299 Jefferson Road
Parsippany, NJ 07054-0677
USA
PHONE (TOLL FREE) +1 800 237 67 45
PHONE +1 973 929 8513
FAX +1 973 929 8503
dynasylan@evonik.com
www.dynasylan.com

Asia / Pacific Evonik Degussa (Shanghai) Co. Ltd.

Inorganic Materials 55, Chungdong Road Shanghai 201108 P.R. China PHONE +86 21 6119 1053 FAX +86 21 6119 1075 dynasylan@evonik.com www.dynasylan.com

Asia / Pacific Evonik Japan Co. Ltd

Inorganic Materials
12th Floor Monolith Building
2-3-1, Nishi-Shinjuku-ku
Tokyo 163-0912
Japan
PHONE +81 353 23 7300
FAX +81 353 23 7399
dynasylan@evonik.com
www.dynasylan.com

Latin America Evonik Brasil Ltda.

Inorganic Materials Alameda Campinas, 579 01404-000 São Paulo-SP Brazil PHONE +55 11 3146 4123 FAX +55 11 3146 4109 dynasylan@evonik.com www.dynasylan.com

Asia / Pacific Evonik Korea Ltd.

Inorganic Materials 94, Galsan 1-dong Bupyeong-gu Incheon, 403-081 Korea PHONE +82 32 510 2433 FAX +82 32 505 2510 dynasylan@evonik.com www.dynasylan.com

Asia / Pacific Evonik India Pvt. Ltd.

Inorganic Materials Krislon House Saki Vihar Road, Anderi (E) Mumbai - 400 072 India PHONE +91 226 7238 800 FAX +91 226 7238 811 dynasylan@evonik.com www.dynasylan.com

