

Dynasylan® GLYMO

3-Glycidyloxypropyltrimethoxysilane

Technical data

Properties and test methods	Value	Unit	Method
Boiling point (0.7 hPa / 0.5 torr)	approx. 90 / 194	°C / °F	DIN 51356
Flash point	approx. 122 / 252	°C / °F	EN 22719
Ignition temperature	approx. 400 / 750	°C / °F	DIN 51794
Viscosity (20 °C / 68 °F)	approx. 3.7 / 3.5	mPa·s / cSt	DIN 53015
Density (20 °C / 68 °F)	approx. 1.07	g/cm ³	DIN 51757
Refractive index n(20, D)	approx. 1.429	-	DIN 51423

Registrations

Dynasylan® GLYMO

DSL/NDSL (Canada):	Yes
PICCS (Philippines):	Yes
TSCA (USA):	Yes
IECSC (P.R. China):	Yes
ENCS (Japan):	Yes
ECL (South Korea):	Yes
EINECS/ELINCS (EU):	Yes
AICS (Australia):	Yes

Dynasylan® GLYMO is a bifunctional organosilane possessing a reactive organic epoxide and hydrolyzable inorganic methoxysilyl groups.

The dual nature of its reactivity allows **Dynasylan®** GLYMO to bind chemically to both inorganic materials (e.g. glass, metals, fillers) and organic polymers (e.g. thermosets, thermoplastics, elastomers), thus functioning as an adhesion promoter, crosslinking agent and/or surface modifier.

Dynasylan® GLYMO is a colorless low-viscosity liquid with a slight terpentine-like odor. It is soluble in alcohols, ketones and aliphatic or aromatic hydrocarbons.

Safety and handling

Before considering the use of Dynasylan® and Protectosil® products please read its Material Safety Data sheet (MSDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use. The Material Safety Data Sheet is available after registration on our website www.dynasylan.com or upon request from your local representative, customer service or from Evonik Industries AG, Product Safety Department, E-MAIL sds-im@evonik.com.

Packaging and storage

Dynasylan® GLYMO is supplied in 25 kg, 200 kg, and 210 kg drums and 950 kg bulk containers. In the unopened container **Dynasylan®** GLYMO has a shelf life of at least one year.

Properties and application

Dynasylan[®] GLYMO is an essential ingredient in the products of many industries. Examples are:

- glass fiber/glass fabric composites: as a finish or a size ingredient
- foundry resins: as an additive to polyurethane resins
- sealants and adhesives: as a primer or additive
- mineral filled composites: for pretreatment of fillers and pigments or as an additive to the polymer
- paints and coatings: as an additive and as a primer for improving adhesion to the substrate, especially glass and metal
- improved shelf life over aminosilanes in polyurethanes

Important product effects that can be achieved through the use of **Dynasylan**[®] GLYMO include:

- improved mechanical properties, such as flexural strength, tensile strength, impact strength and modulus of elasticity
- improved moisture and corrosion resistance
- improved electrical properties, for example dielectric constant, volume resistivity

Dynasylan[®] GLYMO can also improve such processing properties as

- filler dispersion
- rheological behavior (i.e. viscosity reduction) Newtonian behavior
- increased filler loading
- non yellowing

Reactivity

In the presence of water, the methoxy groups of **Dynasylan**[®] GLYMO hydrolyze to form reactive silanol groups which can bond to a variety of inorganic substrates. The organophilic glycidyl end of **Dynasylan**[®] GLYMO can react with a suitable polymer. Hydrolysis of **Dynasylan**[®] GLYMO can be catalyzed by organic acids such as acetic acid. Examples of suitable inorganic substrates are glass, glass fibers, quartz, cristobalite and metals. **Dynasylan**[®] GLYMO may be used with such polymers as epoxy, phenolic, polyurethanes, PVAC, acrylates, polysulfides.

Processing

Dynasylan[®] GLYMO may be used as a constituent of an aqueous size, neat, or added to the polymer matrix as an additive. A chemical modification can be achieved by reaction with suitable functional monomers or polymers.

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. EVONIK DISCLAIMS ALL REPRESENTATIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, AND SHALL HAVE NO LIABILITY FOR, MERCHANTABILITY OF THE PRODUCT OR ITS FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE), OR OTHERWISE. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used.

Europe/Middle-East/Africa/RoW

Evonik Industries AG

Inorganic Materials
Rodenbacher Chaussee 4
63457 Hanau-Wolfgang
Germany
PHONE +49 6181 59 13636
FAX +49 6181 59 13737
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik Degussa (SEA) Pte. Ltd.

Inorganic Materials
3 Internatioanl Business Park
#07-18, Nordic European Centre
Singapore 609927
PHONE +65 6809 6830
FAX +65 6809 6630
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik Taiwan Ltd.

Inorganic Materials
Artist Construction Bldg.
9F, No. 133
Min Sheng East Road, Sec 3
Taipei, 105 Taiwan, R.O.C.
Taiwan
PHONE +886 227 17 1242
FAX +886 227 17 2106
dynasytan@evonik.com
www.dynasytan.com

North America

Evonik Degussa Corporation

Inorganic Materials
P.O. Box 677
299 Jefferson Road
Parsippany, NJ 07054-0677
USA
PHONE (TOLL FREE) +1 800 237 67 45
PHONE +1 973 929 8513
FAX +1 973 929 8503
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik Degussa (Shanghai) Co. Ltd.

Inorganic Materials
55, Chungdong Road
Shanghai 201108
P.R. China
PHONE +86 21 6119 1053
FAX +86 21 6119 1075
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik Japan Co. Ltd

Inorganic Materials
12th Floor Monolith Building
2-3-1, Nishi-Shinjuku-ku
Tokyo 163-0912
Japan
PHONE +81 353 23 7300
FAX +81 353 23 7399
dynasytan@evonik.com
www.dynasytan.com

Latin America

Evonik Brasil Ltda.

Inorganic Materials
Alameda Campinas, 579
01404-000 São Paulo-SP
Brazil
PHONE +55 11 3146 4123
FAX +55 11 3146 4109
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik Korea Ltd.

Inorganic Materials
94, Galsan 1-dong
Bupyeong-gu
Incheon, 403-081
Korea
PHONE +82 32 510 2433
FAX +82 32 505 2510
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik India Pvt. Ltd.

Inorganic Materials
Krislon House
Saki Vihar Road, Anderi (E)
Mumbai - 400 072
India
PHONE +91 226 7238 800
FAX +91 226 7238 811
dynasytan@evonik.com
www.dynasytan.com