

VINNOL® H 15/50

VINYL CHLORIDE COPOLYMER, CAS NO. 9003-22-9

Product description

VINNOL® H 15/50 is a copolymer of approx. 85 wt.% vinyl chloride (VC) and approx. 15 wt.% of vinyl acetate (VAc). Its main use is as a binder for surface coating compounds and printing inks.

Properties

VINNOL® H 15/50 is a thermoplastic, physically drying binder that forms a film when the solvent contained in the formulation has evaporated.

Like all VC copolymers, VINNOL® H 15/50 is extremely tough, showing permanent flexibility, abrasion resistance, little tendency to swell in the presence of water and low gas permeability. It is also highly resistant to oil, grease, dilute aqueous acids, alkalis and saline solutions, as well as to aliphatic hydrocarbons, such as white spirit, and alcohols.

Application

Typical applications for VINNOL® H 15/50:

- Heat-sealable lacquers
- Printing inks
- Paper and film coatings
- Protective and masonry paints
- Strippable lacquers

Processing

VINNOL® H 15/50 is generally used in dissolved form.

Ketones and esters are the solvents most commonly used for VINNOL® H 15/50, ketones being more efficient than esters.

Of the chlorinated hydrocarbons, methylene chloride and 1,2-dichloroethane are true solvents, while tri- and tetrachloroethene have only a swelling effect.

Alcohols and aliphatic hydrocarbons do not dissolve VINNOL® H 15/50. Aromatic hydrocarbons may be combined to a limited extent with true solvents.

VINNOL® H 15/50 can be plasticized with monomeric and polymeric plasticizers, such as phthalates, adipates, sebacates, citrates, phosphates, epoxides and chlorinated paraffins.

VINNOL® H 15/50 is fully compatible with all other VINNOL® surface coating resins. It also combines well with many acrylic polymers and ketone resins, as well as with some epoxides. Alkyd resins, nitrocellulose, polyvinyl acetates and polyvinyl butyrals are in general incompatible with VINNOL® H 15/50.

We recommend always checking the compatibility of VINNOL® H 15/50 with the polymer in question.

VINNOL® H 15/50 shows good compatibility with pigments routinely used in the coatings industry. Care must be taken when using pigments containing zinc or cadmium because these catalyze the decomposition of VC copolymers at elevated temperatures. The same applies to iron-oxide pigments.

Despite good inherent stability, it is necessary for some applications to stabilize coatings based on VINNOL® H 15/50 against heat and/or UV light. Epoxy compounds often suffice to stabilize these coatings against low thermal impact. Where higher temperatures are involved, it is advisable to use calcium/zinc or organotin stabilizers.

Outdoor applications require the additional use of UV stabilizers along with thermal stabilizers optimized for these conditions.

To avoid risk of discoloration, contact with iron should be avoided both during preparation of the solution and during subsequent storage of the product. VINNOL®-based surface-coating resins should be stored in coated containers.

Storage

Store VINNOL® H 15/50 under dry conditions and at room temperature (below 25 °C). Under these conditions, the product has a shelf life of at least 12 months, from the delivery date. If the material is kept beyond the recommended shelf life, it is not necessarily unusable, but the user should perform a quality control on the properties relevant to the application.

The properties determined in our pre-release quality control may change during storage, depending on storage conditions, and deviate from the specification.

Packaging

VINNOL® H 15/50 is packed in 25-kg, coated three-ply paper bags containing a polyethylene liner.

If VINNOL® H 15/50 is used in applications other than those mentioned, the choice, processing and use of VINNOL® H 15/50 is the sole responsibility of the purchaser. All legal and other regulations must be complied with.

Additional information

VINNOL® H 15/50 can be used for applications with food contact in compliance with FDA 21 CFR §175.105 and §175.300.

Comprehensive information regarding evaluation with respect to other food contact regulations may be requested from our account managers and Wacker subsidiaries.

Safety notes

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. These are available on request from WACKER sales offices or may be downloaded from the WACKER Web site www.wacker.com/vinnol.

Product data

Specification data	Inspection Method	Value
Chlorine content	specific method	47,7 - 48,9 wt. %
K-value	DIN EN ISO 1628-2	49 - 51
Volatiles	specific method	< 1,0 wt. %
Viscosity ¹⁾ (20% solids in MEK)	DIN 53015 (20°C)	60 - 80 mPa*s

Typical general characteristics	Inspection Method	Value
Efflux time (20% in MEK)	DIN EN ISO 2431 (4 mm)	approx. 66 s
Supply form	Visual	white powder
Particle size	specific method	< 1,0 mm
Bulk density	DIN EN ISO 60	approx. 750 kg/m³
Density	DIN 66137-2	1,37 g/cm³
Glass transition temperature	DSC (DIN 53765 / ISO 11357-5)	approx. 74 °C
Molecular weight (M _V)	SEC, PS-Standard	60000 - 80000

¹⁾ after dissolving at 50°C

Figures below "Typical general characteristics" are intended as a guide and should not be used in preparing specifications.

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.

The management system has been certified according to DIN EN ISO 9001 and DIN EN ISO 14001

WACKER® is a trademark of Wacker Chemie AG. VINNOL® is a trademark of Wacker Chemie AG.

For technical, quality, or product safety questions, please contact:

Wacker Chemie AG
Hanns-Seidel-Platz 4
81737 München, Germany
info@wacker.com

www.wacker.com