

Evonik CYRO MHOROMER® BM 905 2-Hydroxyethyl Methacrylate

Category : Polymer , Thermoset , Methacrylate

Material Notes:

Application: Adhesion promoter for polymers. Thermosetting paints. Hydrophilic polymers. Light-curing polymer systems. Appearance:

Clear, colorless liquid. Odor: Ester-like CAS: 868-77-9 Information Provided by Evonik CYRO

Order this product through the following link:

http://www.lookpolymers.com/polymer_Evonik-CYRO-MHOROMER-BM-905-2-Hydroxyethyl-Methacrylate.php

Physical Properties	Metric	English	Comments
Density	1.07 g/cc	0.0387 lb/in ³	
Viscosity	5.0 cP	5.0 cP	
	@Temperature 30.0 °C	@Temperature 86.0 °F	
Molecular Weight	130.1 g/mol	130.1 g/mol	
Vapor Pressure	0.000100 bar	0.0750 torr	
	@Temperature 20.0 °C	@Temperature 68.0 °F	

Thermal Properties	Metric	English	Comments
Boiling Point	250 °C	482 °F	
	@Pressure 0.1013 MPa	@Pressure 14.69 psi	
Flash Point	101 °C	214 °F	DIN 51758

Optical Properties	Metric	English	Comments
Refractive Index	1.453	1.453	
	@Temperature 20.0 °C	@Temperature 68.0 °F	

Chemical Properties	Metric	English	Comments
Acid Value	<= 0.10	<= 0.10	Rohm Method: M4 (acid-base titr., MAAC)

Processing Properties	Metric	English	Comments
Moisture Content	<= 0.10 %	<= 0.10 %	Rohm Method: M3 (according to K. Fischer)

Descriptive Properties	Value	Comments
Color	max. 30	Rohm Method: M5 (Pt-Co)

Degree of Purity (%) Descriptive Properties	min. 98 Value	Rohm Method: M2-8 (GC) Comments
Ethyleneglycol dimethacrylate (%)	max. 0.2	Rohm Method: M2-8 (GC)
Heat of Polymerization (kJ/mol)	50	
MEHQ	180-220	ppm, Rohm Method: M1-1 (HPLC), MEHQ
Polyethyleneglycol monomethacrylates (%)	max. 1.5	Rohm Method: M2-8 (GC)
Solidification Point (°C)	below -60	
Solubility (%)	miscible with water in any ratio	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China