

Evonik CYRO MHOROMER® D 1067 Benzyl Methacrylate

Category : Polymer , Thermoset , Methacrylate

Material Notes:

Application: Base product for reactive adhesives. Appearance: Clear, colorless liquid. Odor: Ester-like CAS: 2495-37-6 Information Provided by Evonik CYRO

Order this product through the following link:

http://www.lookpolymers.com/polymer_Evonik-CYRO-MHOROMER-D-1067-Benzyl-Methacrylate.php

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in ³	
Viscosity	4.0 cP @Temperature 20.0 °C	4.0 cP @Temperature 68.0 °F	
Molecular Weight	179 g/mol	179 g/mol	

Thermal Properties	Metric	English	Comments
Boiling Point	232 °C @Pressure 0.1013 MPa	450 °F @Pressure 14.69 psi	
Flash Point	107 °C	225 °F	DIN 51758

Optical Properties	Metric	English	Comments
Refractive Index	1.513 @Temperature 20.0 °C	1.513 @Temperature 68.0 °F	

Chemical Properties	Metric	English	Comments
Acid Value	<= 0.020	<= 0.020	Rohm Method: M4 (acid-base titr., MAAC)

Processing Properties	Metric	English	Comments
Moisture Content	<= 0.10 %	<= 0.10 %	Rohm Method: M3 (according to K. Fischer)

Descriptive Properties	Value	Comments
Color	max. 50	Rohm Method: M5 (Pt-Co)
Degree of Purity (%)	min. 98	Rohm Method: M2-182 (GC)
MEHQ	45-55	ppm, Rohm Method: M1-1 (HPLC), MEHQ

Solubility (%) Descriptive Properties	insoluble in water Value	Comments
--	-----------------------------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China