

Dynasytan® SILBOND® 50

Ethyl polysilicates

Technical Data

Properties and test methods	Unit	Value
Form	-	Clear Liquid
Density (20 °C)	g/cm ³	1.095-1.150
Viscosity (20 °C)	mPa·s / cSt	5.0
Flash Point	°C / °F	27 / 81
Boiling Point	°C / °F	160 / 320
Silica Content (as SiO ₂)	% by wt	45.0 - 47.0

Dynasytan® SILBOND® 50 is a clear, low-viscosity liquid that is one of the most concentrated forms of available silica, ranging from 45.0% to 47.0% (the Si content of Dynasytan® SILBOND® 50 is calculated as SiO₂).

Dynasytan® SILBOND® 50 is an ethyl polysilicate that is the partially hydrolyzed product of tetraethyl orthosilicate (TEOS). The partial hydrolysis of TEOS (Si[OEt]₄) results in the conversion of ethoxy groups to hydroxyl groups forming silanols. Subsequent condensation of silanols will form siloxane bonds (-Si-O-Si-O-) and eventually cause the material to gel.

Dynasytan® SILBOND® 50 is often used as an intermediate, which is further hydrolyzed to produce a binder that can be used for many applications. This binder is used for inorganic zinc-rich primers, investment casting molds, cores and ceramic shapes, and coatings.

Safety and handling

Before considering the use of Dynasytan® SILBOND® products please read its Safety Data Sheet (SDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use. The Safety Data Sheet is available after registration on our website www.dynasytan.com or upon request from your local representative, customer service or from Evonik Resource Efficiency GmbH, Product Safety Department, E-MAIL sds-hu@evonik.com.

Packaging, storage and shelf life

Dynasytan® SILBOND® 50 could be available in pails, drums, totes, and tanker quantities.

In the unopened container Dynasytan® SILBOND® 50 has a shelf life of min. 12 months from date of manufacture.

Please ask us for further details.

Properties and applications

Similar to Dynasylan® SILBOND® Condensed and Dynasylan® SILBOND® 40, Dynasylan® SILBOND® 50 is used to deposit silicic acid formed as a result of complete hydrolysis. The resulting silicic acid bonds well to many inorganic substrates, such as glass, ceramic, metal, fillers, pigments, and synthetic fibers.

The deposition of a thin SiO₂ layer improves the chemical and thermal stability and mechanical properties.

Other applications are:

- binder, especially for inorganic zinc-rich coatings or precision investment castings
- encapsulant for hydroxyl poor fillers to enhance adhesion with functional silanes
- crosslinker component in cold-curing silicone rubber systems
- coupling agent/adhesion promoter between organic polymers and inorganic substrates (fillers, pigments, glass, metals surfaces, etc.)

Dynasylan® SILBOND® 50 can also be used as starting material for sol-gel processes. It is usually used in conjunction with alkylsilanes (e.g. Dynasylan® MTES) organofunctional silanes and/or organic precursors (e.g. organic resins) to form siloxane networks. This makes it possible to obtain highly scratch-, abrasion-, and chemical-resistant coatings.

Dynasylan® SILBOND® 50 is immiscible with water, therefore hydrolysis requires a cosolvent as a solubilizer. Mineral acids and ammonia are suitable as catalysts.

Dynasylan® SILBOND® 50 or its hydrolysates are also the binder component for 1- and 2-pack inorganic zinc-rich coatings, for corrosion protection on steel, and for slurries used in precision investment castings.

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

Europe/Middle-East/Africa/RoW

Evonik Resource Efficiency GmbH

Business Line Silanes
Rodenbacher Chaussee 4
63457 Hanau-Wolfgang
Germany
PHONE +49 6181 59 13636
FAX +49 6181 59 713915
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik (SEA) Pte. Ltd.

Business Line Silanes
3 Internatioanl Business Park
#07-18, Nordic European Centre
Singapore 609927
PHONE +65 6809 6576
FAX +65 6809 6699
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik Japan Co. Ltd

Business Line Silanes
12th Floor Monolith Building
2-3-1, Nishi-Shinjuku-ku
Tokyo 163-0912
Japan
PHONE +81 353 23 7446
FAX +81 353 23 7397
dynasytan@evonik.com
www.dynasytan.com

North America

Evonik Corporation

Business Line Silanes
299 Jefferson Road
Parsippany, NJ 07054-0677
USA
PHONE (TOLL FREE) +1 800 237 67 45
PHONE +1 973 929 8513
FAX +1 973 929 8503
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik Specialty Chemicals (Shanghai) Co. Ltd.

Business Line Silanes
55, Chungdong Road
Xinzhuang Industry Park
Shanghai 201108
P.R. China
PHONE +86 21 61191-399
FAX +86 21 61191-648
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik India Pvt. Ltd.

Business Line Silanes
Krislon House
Saki Vihar Road, Anderi (E)
Mumbai - 400 072
India
PHONE +91 226 7238 809
FAX +91 226 7238 811
dynasytan@evonik.com
www.dynasytan.com

North America

Silbond Corporation

9901 Sand Creek Highway
Weston, MI 49289
USA
PHONE +1 517 436 9316
FAX +1 517 436 3148
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik Korea Ltd.

Business Line Silanes
94, Galsan 1-dong
Bupyeong-gu
Incheon, 403-081
Korea
PHONE +82 2320 4773
FAX +82 2783 2520
dynasytan@evonik.com
www.dynasytan.com

Latin America

Evonik Brasil Ltda.

Business Line Silanes
Alameda Campinas, 579
01404-000 São Paulo-SP
Brazil
PHONE +55 11 3146 4123
FAX +55 11 3146 4148
dynasytan@evonik.com
www.dynasytan.com

Asia / Pacific

Evonik Taiwan Ltd.

Business Line Silanes
Artist Construction Bldg.
9F, No. 133
Min Sheng East Road, Sec 3
Taipei, 105 Taiwan, R.O.C.
Taiwan 10596
PHONE +886 227 17 1242
FAX +886 227 17 2106
dynasytan@evonik.com
www.dynasytan.com