

## AERODISP® W 740 X

### Aqueous dispersion of hydrophilic fumed titanium dioxide (TiO<sub>2</sub>)

#### Characteristic physico-chemical data

Properties and test methods	Unit	Value
TiO <sub>2</sub> content based on ignited material	%	39 - 41
Viscosity measured at a shear rate of 100 s <sup>-1</sup>	mPa s	≤ 30
pH value		5.0 - 7.0
Density 20 °C	g/cm <sup>3</sup>	1.41
Particle size (d <sub>50</sub> ) Static light scattering	nm	70

The data represents typical values (no product specification)

#### Registrations (substance or product components)

##### AERODISP® W 740 X

CAS-No.*	13463-67-7
EINECS (Europe)	registered
ENCS (Japan) IECSC (China) CSNN (Taiwan) PICCS (Philippines)	registered
NZIoC (New Zealand)	registered

\*CAS-No. refers to the main inorganic substance used

AERODISP® W 740 X is an aqueous dispersion of titanium dioxide with a very high solid content and weakly acidic pH value. The dispersion appears milky white.

#### Applications and properties

##### Properties

- Very high solid content (40 %)
- Very high (photo)catalytic activity when irradiated with UV light
- Good transparency in thin layers
- High chemical purity
- Outstanding rheological properties
- Easy handling
- Can be added simply to water-based formulations

##### Applications

- Catalyst and catalyst substrate
- Photocatalyst
- Ceramic bonding agent and raw material / additive for the formulation of ceramics

## Safety and handling

Information concerning the safety of this product is listed in the corresponding Safety Data Sheet, which will be sent with the first delivery or upon updating. Such information is also available from Evonik Resource Efficiency GmbH, Product Safety Department, E-MAIL [sds-hu@evonik.com](mailto:sds-hu@evonik.com) or can be downloaded from our homepage [www.aerosil.com](http://www.aerosil.com). We recommend to read carefully the safety data sheet prior to the use of our product.

## Packaging and storage

Depending on the region, AERODISP® W 740 X is available in 60 kg containers, 220 kg drums and 1250 kg intermediate bulk containers (IBC's). All dispersions must be protected from extreme heat and frost. The product should be used within 12 months from the date of production. Small amounts of sedimentation are normal.

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

### Customer Service

#### Europe/ Middle-East/ Africa/ Latin America

**Evonik Resource Efficiency GmbH**  
Business Line Silica  
PB 010-A410  
Rodenbacher Chaussee 4  
63457 Hanau-Wolfgang  
Germany  
PHONE +49 6181 59 12532  
FAX +49 6181 59 712532  
[aerosil@evonik.com](mailto:aerosil@evonik.com)  
[www.aerosil.com](http://www.aerosil.com)

#### North America

**Evonik Corporation**  
Business Line Silica  
299 Jefferson Road  
Parsippany, NJ 07054-0677  
USA  
PHONE +1 800-233-8052  
FAX +1 973-929-8502  
[aerosil@evonik.com](mailto:aerosil@evonik.com)  
[www.aerosil.com](http://www.aerosil.com)

#### Asia (excluding Japan)

**Evonik (SEA) Pte. Ltd.**  
Business Line Silica  
3 International Business Park  
Nordic European Centre, #07-18  
Singapore 609927  
PHONE +65 6809-6877  
FAX +65 6809-6677  
[aerosil@evonik.com](mailto:aerosil@evonik.com)  
[www.aerosil.com](http://www.aerosil.com)

#### Japan

**NIPPON AEROSIL CO., LTD.**  
Marketing & Sales Division  
P.O. Box 7015  
Shinjuku Monolith 13F  
3-1, Nishi-Shinjuku 2-chrome  
Shinjuku-ku, Tokyo  
163-0913 Japan  
PHONE +81 3 3342-1789  
FAX +81 3 3342-1761  
[infonac@evonik.com](mailto:infonac@evonik.com)  
[www.aerosil.jp](http://www.aerosil.jp)

### Technical Service

#### Europe/ Middle-East/ Africa/ Latin America

**Evonik Resource Efficiency GmbH**  
Business Line Silica  
HPC 911-221 A  
Rodenbacher Chaussee 4  
63403 Hanau-Wolfgang  
Germany  
PHONE +49 6181 59-3936  
FAX +49 6181 59 4489  
[technical.service.aerosil@evonik.com](mailto:technical.service.aerosil@evonik.com)  
[www.aerosil.com](http://www.aerosil.com)

#### North America

**Evonik Corporation**  
Business Line Silica  
2 Turner Place  
Piscataway, NJ 08855-0365  
USA  
PHONE +1 888 SILICAS  
PHONE +1 732 981-5000  
FAX +1 732 981-5275  
[technical.service.aerosil@evonik.com](mailto:technical.service.aerosil@evonik.com)  
[www.aerosil.com](http://www.aerosil.com)

#### Asia (excluding Japan)

**Evonik Specialty  
Chemicals (Shanghai) Co.,Ltd**  
Business Line Silica  
55 Chundong Road  
Xinzhuang Industry Park  
Shanghai 201108  
P.R. China  
PHONE +86 21 6119-1065  
FAX +86 21 6119-1075  
[technical.service.aerosil@evonik.com](mailto:technical.service.aerosil@evonik.com)  
[www.aerosil.com](http://www.aerosil.com)

#### Japan

**NIPPON AEROSIL CO., LTD.**  
Applied Technology Group  
3 Mita-Cho  
Yokkaichi, Mie  
510-0841 Japan  
PHONE +81 59 345-5270  
FAX +81 59 346-4657  
[infonac@evonik.com](mailto:infonac@evonik.com)  
[www.aerosil.jp](http://www.aerosil.jp)