

Evonik Corporation VESTOWAX® C 60 Fischer-Tropsch Wax

Category : Polymer

Material Notes:

VESTOWAX is synthetic waxes produced essentially by two different processes, the Ziegler polymerization and the Fischer-Tropsch process. The Ziegler polymerization of ethylene synthesizes polyethylene waxes with different densities and molecular weights depending on the preparation conditions. The Fischer Tropsch process yields straight chain products possessing low viscosity in the melt and having molecular weights between 500 and 1000g/mol. This formulation is an oxidate.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Evonik-Corporation-VESTOWAX-C-60-Fischer-Tropsch-Wax.php

Physical Properties	Metric	English	Comments
Density	0.960 g/cc @Temperature 23.0 °C	0.0347 lb/in ³ @Temperature 73.4 °F	DIN 53 479
Viscosity	<= 20 cP @Temperature 120 °C	<= 20 cP @Temperature 248 °F	DIN 52 007/1

Mechanical Properties	Metric	English	Comments
Penetration	4.0 - 6.0	4.0 - 6.0	number in mm, 10-1; DGF M-III 9b

Thermal Properties	Metric	English	Comments
Dropping Point	98.0 - 102 °C	208 - 216 °F	DGF M-III 3

Chemical Properties	Metric	English	Comments
Total Acid Number	29 - 34	29 - 34	mg KOH/g; DGF M-IV 2

Descriptive Properties	Value	Comments
Color	white	
Saponification Number [mg KOH/g]	50-62	DGF M-IV 2

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China