

INFINO EF-1032

Extrusion resin of non-halogen flame-retardant characteristic

Flammability	Flammability	V-0	UL94	mm	1,5
Physical	Specific Gravity	Natural or Representative Color	ISO 1183	-	1,19
	Melt Flow Index	250°C,10kg	ISO 1133	g/10min	20
Thermal	Heat Deflection Temperature (unannealed)	1.8 MPa, 4.0mm	ISO 75-2	°C	92
	Heat Deflection Temperature (unannealed)	0.45 MPa, 4.0mm	ISO 75-2	°C	101
	Vicat Softening Temperature	B/50	ISO R 306	°C	107
	Vicat Softening Temperature	B/120	ISO R 306	°C	129
Mechanical	Tensile Strength at Yield	50mm/min	ISO 527	MPa	65
	Tensile Strain at Break	50mm/min	ISO 527	%	73
	Tensile Modulus	50mm/min	ISO 527	MPa	2400
	Tensile Strength at Break	50mm/min	ISO 527	MPa	55
	Flexural Strength	2mm/min	ISO 178	MPa	95
	Flexural Modulus	2mm/min	ISO 178	MPa	2400
	Izod Impact Strength (notched)	at 23°C, 4mm	ISO 180 1A	KJ/m ²	53
	Charpy Impact Strength (V-notched)	23°C, 4mm	ISO 179 1eA	KJ/m ²	62
	Rockwell Hardness	R-scale	ISO 2039-2	-	120

All values are approximate values and are given after the best knowledge and conscience. Hence, because of variable processing terms or processing procedures an obligation cannot be derived from it.

Tekuma Kunststoff GmbH is not the manufacturer of a.m. product. The information returns the result of the quality inspection. An assurance of certain properties and qualities for specific uses cannot be derived. We recommend additional tests with regard to the

TEKUMA KUNSTSTOFF GMBH

Röntgenstraße 2 21465 Reinbek Germany Telefon +49 40 727 702 - 0 Fax +49 40 722 89 69 info@tekuma.de
Geschäftsführer Constantin Maul Registergericht Lübeck HRB 1387 RE Ust-IdNr. DE135102242 St.Nr. 30 292 15675

www.tekuma.de



suitability ability. Guarantee occurs within the scope of our general terms of sale and terms of delivery.