

INFINO NH-1027 HF

Flammability	Flammability	HB	UL94	mm	1
	Flammability	V-2	UL94	mm	1.2, 1.5, 3.0
	Flammability	V-0	UL94	mm	1.2, 1.5, 3.0
	Flammability	5VB	UL94	mm	1.5, 3.0
	Flammability	V-1	UL94	mm	1
Physical	Specific Gravity	Natural or Representative Color	ISO 1183	-	1,19
	Melt Flow Index	220°C, 10kg	ISO 1133	g/10min	55
Thermal	Heat Deflection Temperature (unannealed)	1.8 MPa, 4.0mm	ISO 75-2	°C	82
	Heat Deflection Temperature (unannealed)	0.45 MPa, 4.0mm	ISO 75-2	°C	92
	Heat Deflection Temperature (annealing)	1.8 MPa, 4.0mm	ISO 75-2	°C	90
	Heat Deflection Temperature (annealing)	0.45 MPa, 4.0mm	ISO 75-2	°C	96
	Vicat Softening Temperature	B/50	ISO R 306	°C	98
	Vicat Softening Temperature	B/120	ISO R 306	°C	101
Mechanical	Tensile Strength at Yield	50mm/min	ISO 527	MPa	61
	Tensile Strain at Break	50mm/min	ISO 527	%	39
	Tensile Modulus	50mm/min	ISO 527	MPa	2400
	Tensile Strength at Break	50mm/min	ISO 527	MPa	49
	Flexural Strength	2mm/min	ISO 178	MPa	92
	Flexural Modulus	2mm/min	ISO 178	MPa	2600
	Izod Impact Strength (notched)	at 23°C, 4mm	ISO 180 1A	KJ/m ²	17
	Charpy Impact Strength (V-notched)	23°C, 4mm	ISO 179 1eA	KJ/m ²	17

All values are approximate values and are given after the best knowledge and conscience. Hence, because of variable processing terms or processing procedures an obligation cannot be derived from it.

Tekuma Kunststoff GmbH is not the manufacturer of a.m. product. The information returns the result of the quality inspection. An assurance of certain properties and qualities for specific uses cannot be derived. We recommend additional tests with regard to the suitability. Guarantee occurs within the scope of our general terms of sale and terms of delivery.