

GALSTAFF MULTIRESINE

SPECIALITY RESINS AND AUXILIARIES

Data Sheet

Date of Issue: May 10th 2015

Rev. : 03

FTALON 32/75 MIBK

Saturated polyester for wood, metal and paper

CHARACTERISTICS (INTERNAL METHODS)

• Solvent	MIBK
• Appearance	Clear
• Solid content	74 – 76 %
• Acid value, on solid	20 - 28 mgKOH/g
• Gardner Viscosity, at 25°C	Z1 – Z3
• Gardner Colour	max 4
• (*) OH %	~3.3

(*) Typical properties not guaranteed

APPLICATIONS

FTALON 32 is a saturated polyester suitable for basecoats and topcoats with forced air-drying.

FTALON 32's main characteristics are :

- good body;
- excellent mechanical resistance;
- outstanding surface hardness.

COMPATIBILITY/SOLUBILITY

FTALON 32 is compatible with FTALON resins, nitrocellulose and the plasticisers, urea and melamine resins; it is partially compatible with castor oil.

FTALON 32 is soluble in aromatic solvents, acetates and ketones. It is insoluble in aliphatics.

However, due to the huge number of potential partners, preliminary tests are recommended.

SHELF LIFE AND STORAGE

FTALON 32 has a shelf life of 12 months from the production date, if stored in original, sealed container, in protected areas.

For all information related to handling and toxicological knowledge, please refer to the Safety Data Sheet.

galstaff

QUALIFYING
50
YEARS
COATINGS



The above mentioned data are issued according to our best knowledge and expertise yet they are provided without guarantee.

I - 21020 MORNAGO - VIA STAZIONE, 90 TEL +39 0331 9014-1 – FAX.+ 39 0331 903777 – E-mail: sales@galstaffmultiresine.com

Web site: www.galstaffmultiresine.com