

# GALSTAFF MULTIRESINE

SPECIALITY RESINS AND AUXILIARIES

Data Sheet

Date of Issue: June 3<sup>rd</sup> 2012

Rev. : 02

## FTALON 29

Saturated polyester with fast solvent release

### CHARACTERISTICS (INTERNAL METHODS)

• Solid content	49 – 51 %	59 – 61 %
• Solvent	Xylene	Butyl Acetate
• Acid value, on solid	14 - 20 mgKOH/g	14 - 20 mgKOH/g
• Gardner Viscosity, at 25°C	X - Z <sub>1</sub>	X - Z
• Gardner Colour	max. 5	max. 5
• (*) OH %	~3.3	~3.3

(\*) Typical properties not guaranteed

### APPLICATIONS

FTALON 29 is a saturated polyester characterized by fast solvent release and good flowing. Its main applications are in sanding primers or in matt finishes by spraying or curtain coater, with fast drying-time both at room temperature and forced temperature (45-50°C). In those applications, FTALON 29 can be used with FTALON 28 or 41 (plasticizing), obtaining hard and resistant films.

### COMPATIBILITY/SOLUBILITY

FTALON 29 is compatible with FTALON resins, nitrocellulose, isocyanates and isocyanurates. FTALON 29 is soluble in aromatics, esthers and ketones; it is insoluble in aliphatics and alcohols. However, due to the huge number of potential partners, preliminary tests are recommended.

### SHELF LIFE AND STORAGE

FTALON 29 has a shelf life of 12 months from the production date, if stored in original, sealed container, in protected areas. For all information related to handling and toxicological knowledge, please refer to the Safety Data Sheet.

**galstaff**



The above mentioned data are issued according to our best knowledge and expertise yet they are provided without guarantee.

I - 21020 MORNAGO - VIA STAZIONE, 90 TEL +39 0331 9014-1 – FAX.+ 39 0331 903777 – E-mail: [sales@galstaffmultiresine.com](mailto:sales@galstaffmultiresine.com)

Web site: [www.galstaffmultiresine.com](http://www.galstaffmultiresine.com)