

GALSTAFF MULTIRESINE

SPECIALITY RESINS AND AUXILIARIES

Data Sheet

Date of Issue: October 6th 2011

DP-ITALESTER CM3 Saturated polyester for cosmetic

CHARACTERISTICS (INTERNAL METHODS)

• Appearance	Clear
• Gardner Colour	1 max
• Gardner Viscosity	Z – Z2
• Brookfield Viscosity, at 25°C	3500 – 4500 mPa.s
• Acid value	40 – 55 mg KOH/g
• Solid Content	68 – 72 %
• Aromatics	50 ppm, max

APPLICATIONS

DP-ITALESTER CM3 is a saturated polyester used as plasticizer in nitrocellulose systems for cosmetic.

COMPATIBILITY

DP-ITALESTER CM3 is compatible with nitrocellulose.
However, please verify previously with preliminary tests.

SHELF LIFE AND STORAGE

DP-ITALESTER CM3 has a shelf life of 12 months from the production date, if stored in original, sealed container, in protected areas.

For all information related to handling and toxicological knowledge, please refer to the Safety Data Sheet.

galstaff

QUALIFYING
5
YEARS
COATINGS

MR

The above mentioned data are issued according to our best knowledge and expertise yet they are provided without guarantee.

I - 21020 MORNAGO - VIA STAZIONE, 90 TEL +39 0331 9014-1 – FAX.+ 39 0331 903777 – E-mail: sales@galstaffmultiresine.com

Web site: www.galstaffmultiresine.com