

GALSTAFF MULTIRESINE

SPECIALITY RESINS AND AUXILIARIES

SYNTEVEN 422

Product description

SYNTEVEN 422 is a styrenic orthophthalic unsaturated polyester resin, amine promoted, with high reactivity and high stability properties.

Application

SYNTEVEN 422 is used as basic binder in the manufacturing of several kinds of mastics which have good curing properties and constancy of colour after polymerization.

Properties

SYNTEVEN 422 is a cold-curing resin, even at very low temperatures. After addition of benzoyl peroxide (BPO) it yields a pale and hard polymer. Putties and mastics based on SYNTEVEN 422 cure fully both applied in thick and thin coats. Combinations of talc, dolomite / calcite and powdered barytes with low iron content are suitable as extenders, with talc as the main component because it improves the adhesion to the substrate.

The more spherical extenders such as dolomite, chalk and barytes ensure dense packing.

Specification

<u>Property</u>	<u>Range</u>	<u>Unit of measure</u>	<u>Norm/Method</u>
Iodine colour value	3,0 - 10,0		GA 002.1
Acid value	7,0 - 10,5	mg KOH/g	GA 004.1
Viscosity at 23°C	1500 – 2000	mPa-s	GA 005.1
Non-volatile content	69,0 - 71,0	%	GA 006.1

Additional properties*

<u>Property</u>	<u>Range</u>	<u>Unit of measure</u>	<u>Norm/Method</u>
Density at 20°C	appr. 1,13	g/ml	DIN 53217/2
Curing properties: (50,0g Resin, 1,0g BPO 50%)			GA 019.10
Time from 25°C to 35°C	appr. 7,0	min.	
Time from 25°C to peak	appr. 9,0	min.	
Peak exotherm	appr. 150	°C	
Stability at 25°C	6	months	

*These values provide general information and are not part of the product specification.

Storage

The resin should be stored indoors, in the original packaging, at temperatures between 5°C and 30°C .E xposure to direct sunlight should be avoided. The properties of the product might change during storage.

Safety

Please consult the Safety data sheet before working with this product.

The information contained in this data sheet is based on laboratory data and field experience. We believe this information to be reliable, but do not guarantee its applicability to the user's process or assume any liability for occurrences arising out of its use. The user, by accepting the products described herein, agrees to be responsible for thoroughly testing each such product before committing to production. Our recommendations should not be taken as inducements to infringe any patent or violate any law, safety code or insurance regulation.

Ed: 02/01/2012 Ver 04 Pag. 1/1

