

Technical Data Sheet
Medium Oil Alkyd Resin
AMT602 - X60



Characteristics:

Type of fatty acid	Soya
Solid Content (%)	60±1
Type of Solvent	Xylene
Viscosity (25° C/Gardner)	80 – 120 (Sec)
Color (Gardner)	1 Max
Acid Value (mgKOH/g)	10 Max

Features:

- Very good hardness
- Very good surface and deep drying
- Very good gloss and gloss retention
- Excellent adhesion and flexibility
- Excellent pigment wetting and dispersing
- Very good solvent acceptance

Applications:

- Auto body repair paints
- Industrial machinery coatings
- Metallic paints
- Industrial air-drying paints

Shelf Life:

This product must be stored in its original sealed steel drum in a cold and dry place away from fire, heat source and direct sunlight in temperatures between 5-30°C. Under these conditions, the shelf life of this product will be maximum 12 months from delivery time

Packaging:

190 Kg net in steel drum

Remark:

Solid content, Viscosity and other Qualitative parameters, are customizable based on customer requirements