

# Technical Data Sheet

Short Oil Alkyd Resin

AST701 - X60



Characteristics:

Type of fatty acid	Soya / Sunflower
Solid Content (%)	60±1
Type of Solvent	Xylene
Viscosity (25° C/Gardner)	100 – 200 (Sec)
Color (Gardner)	2 Max
Acid Value (mgKOH/g)	10 Max

Features:

- Very good hardness
- Very good surface and deep drying
- Excellent gloss and gloss retention
- Very good adhesion and flexibility
- Very good pigment wetting and dispersing

Applications:

- Alkyd amin varnishes
- Nitro-cellulose paints and lacquers
- Alkyd amin stoving paints
- Anti-corrosion primers
- Acid curing coatings

Shelf Life:

This product must be stored in its original sealed steel drum in a cold and dry place away from fire, heat source and direct sunlight in temperatures between 5-30°C. Under these conditions, the shelf life of this product will be maximum 12 months from delivery time

Packaging:

200 Kg net in steel drum

Remark:

Solid content, Viscosity and other Qualitative parameters, are customizable based on customer requirements

**Email:** Info@t-sf.info

**Address:** Unit 1105, No. 2, Shahab tower, Ramatia Alley, Valiasr Street, Tehran, Iran

**Phone:** (+98) 21-88714573

**Fax:** (+98) 21-88553720

**GSM.:** (+98) 912-7125145