

Technical Data Sheet

Short Oil Alkyd Resin

AST702 - X60



Characteristics:

Type of fatty acid	Soya
Solid Content (%)	60±1
Type of Solvent	Xylene
Viscosity (25° C/Gardner)	80 – 120 (Sec)
Color (Gardner)	5 Max
Acid Value (mgKOH/g)	12 Max

Features:

- Excellent hardness
- Very good surface and deep drying
- Very good gloss and gloss retention
- Excellent adhesion and flexibility
- Excellent pigment wetting and dispersing
- Very good solvent acceptance

Applications:

- Nitro-cellulose paints enamels
- Stoving paints and lacquers
- Anti-corrosion primers
- Alkyd amin lacquers

Shelf Life:

This product must be stored in its original sealed steel drum in a cold and dry place away from fire, heat source and direct sunlight in temperatures between 5-30°C. Under these conditions, the shelf life of this product will be maximum 12 months from delivery time

Packaging:

200 Kg net in steel drum

Remark:

Solid content, Viscosity and other Qualitative parameters, are customizable based on customer requirements

Email: Info@t-sf.info

Address: Unit 1105, No. 2, Shahab tower, Ramatia Alley, Valiasr Street, Tehran, Iran

Phone: (+98) 21-88714573

Fax: (+98) 21-88553720

GSM.: (+98) 912-7125145