

Technical Data Sheet

Short Oil Alkyd Resin

AST703 - X50



Characteristics:

Type of fatty acid	Soya/Sunflower
Solid Content (%)	50±1
Type of Solvent	Xylene
Viscosity (25° C/Gardner)	40 – 90 (Sec)
Color (Gardner)	3 Max
Acid Value (mgKOH/g)	10 Max

Features:

- Excellent hardness
- Excellent surface and deep drying
- Very good gloss and gloss retention
- Good adhesion and flexibility
- Excellent pigment wetting and dispersing

Applications:

- Hammer finish paints
- Anti-corrosion primers
- Fast dry paints
- Industrial air- drying paints

Shelf Life:

This product must be stored in its original sealed steel drum in a cold and dry place away from fire, heat source and direct sunlight in temperatures between 5-30°C. Under these conditions, the shelf life of this product will be maximum 12 months from delivery time

Packaging:

200 Kg net in steel drum

Remark:

Solid content, Viscosity and other Qualitative parameters, are customizable based on customer requirements

Email: Info@t-sf.info

Address: Unit 1105, No. 2, Shahab tower, Ramatia Alley, Valiasr Street, Tehran, Iran

Phone: (+98) 21-88714573

Fax: (+98) 21-88553720

GSM.: (+98) 912-7125145