

TC-CARBOMER 340

INCI NAME

CARBOMER

Description

TC- CARBOMER 340 is a crosslinked polyacrylate polymer with strong moisturizing ability, acting as high-efficient & low-dosage thickener and suspending agent. It can be neutralized by alkali to form clear gel. Once its carboxyl group is neutralized, molecule chain expands extremely and viscosity comes up, due to mutually exclusion of negative charge. It can enhance yield value and rheology of liquid substances, thus it is easy to get insoluble ingredients (granular, oil drop) suspended at low dosage. It is widely used in O/W lotion and cream as favorable suspending agent.

Specification

Parameter	Value	
Appearance	Fluffy, White Powder	
Viscosity: (mPa.s) (20 rpm at 25°C, Neutralized Solution)	0.2%	19000-35000
	0.5%	40000-70000
Solution Clarity (%Transmission, 420 nm light)	0.2% water solution	≥85
	0.5% water solution	≥85
Residual Benzene (%)	≤0.50	
Residual acrylic acid (%)	≤0.25	
Loss on drying (%)	≤2.0	
Bulk Density (g/100 mL)	19.5-23.5	
Heavy metals	As (ppm)	≤2
	Pb+As+Hg+Sb (ppm)	≤10

These values indicate typical specifications, they are not intended to be used as product specifications.

Properties

High-efficient thickening, suspending and stabilizing ability at low dosage
 Outstanding short flow (non-drip) property
 High clarity
 Resist temperature effect to viscosity

Applications

Clear hydroalcoholic gel .
 lotion and cream
 Hair styling gel
 Shampoo
 Body wash

Formula Guidelines

0.2-1.0%

Cautions

Following operations are forbidden, otherwise result in loss of thickening ability:
 -- Lasting stir or high-shear stir after neutralization
 -- Lasting UV irradiation
 -- Combine with electrolytes

Storage & Handling

Standard Packing: 21kg/box

Storage: Keep in cool, dry, ventilated and lightless place.

Shelf Life: 24 months

GUANGZHOU TINCI MATERIALS TECHNOLOGY CO., LTD.

8th Kangda Road, Yunpu Industrial Zone,
 Huangpu District, Guangzhou, China
 TEL: 86-86-20-82251159 FAX: 86-20-82250169
 WEBSITE: www.tinci.com

Version: A/2
 Last update: 2016-01-12