


SONGNOX™ 3114

Technical Information

1. Components Tris-(3,5-di-tert-butylhydroxybenzyl) isocyanurate



CAS No : 27676-62-6 Mw : 784

2. Properties	Melting Point	218 ~ 223
	Ash (%)	Max. 0.01
	Volatile Loss (%)	Max. 0.20
	Color of solution 425nm (%)	Min. 93.0
	Color of solution 500nm (%)	Min. 97.0
	Assay (%)	Min. 98.0
	Fe Content (ppm)	Max. 10

3. Characteristics & Usages

- * Primary antioxidant for organic polymers
 - * High performance sterically hindered phenolic antioxidant
 - * Low volatility, good color stability, high extraction resistance
 - * For use in color sensitive applications such as polypropylene fiber
 - * Exhibits a synergistic effect when used in combination with a phosphite antioxidants such as SONGNOX™ 1680 or SONGNOX™ 6260.
- Standard blends of SONGNOX™ 3114 and SONGNOX™ 1680 are available.
- * For additional information please consult the Material safety Data Sheet

4. Physical Foam PW (Powder), FF (Free Flow)

5. Packing unit 20Kg Paper Bag, 20Kg PE Bag, 25Kg Carton Box, 50Kg Fiber Drum, 500Kg Flecon Bag